INDUSTRIAL THERMOPLASTIC HOSE





INDUSTRIAL THERMOPLASTIC HOSE PVC, POLYURETHANE & RUBBER BLENDS

Jason Industrial[®] is a Megadyne Group company that manufactures and delivers a comprehensive inventory of rubber and polyurethane synchronous belts, rubber v-belts, industrial hose and couplings, plus hardware to the industrial community worldwide.

When extraordinary needs require specialized components, we will work with you from prototype to production, creating custom solutions that suit your unique application.

As a Jason customer, you can feel confident in the quality and integrity of our products, the speed and efficiency at which they are delivered, and the expertise and customer focus that our local representatives are committed to providing.

Jason's corporate headquarters are based in Fairfield, New Jersey. Our distribution center is located just outside of Chicago, Illinois, with additional corporate offices in Canada, Mexico and Brazil, as well as manufacturing, warehousing and distribution centers in cities across the globe.

Welcome to Jason...the first name in mechanical rubber and urethane products that power industry forward.



TABLE OF CONTENTS



General Information/Technical Reference		Page
Applications Guide		4
Thermoplastic Hose Solutions		2-3
Terms & Conditions		44
Chemical Resistance Tables - PVC, EPDM & Polyurethane		31-43
Product by Market		
Food Hose	Series No.	Page
PU FDA USDA Clear Braided Material Handling Hose - S Ω	3000	19
PVC FDA USDA 3A Clear Suction Hose	3010	20
Material Handling Hose		
PU Lined PVC Material Handling Hose	3020	10
PU Duct and Material Handling Hose	3021	11
PU MD Material Handling Hose	3022	12
PVC Mulch Hose	3030	13
SBR Black Material Handling Hose	3035	14

Petroleum Hose PU Clear Braided Drop Hose - S $\!\Omega$ 3040 6 PU Black Braided Drop Hose $\,$ - $S\Omega$ 3045 7 PU Standard Clear Vapor Recovery Hose - S Ω 3050 8 PU HD Clear Vapor Recovery Hose - S Ω 3053 9 NBR/PVC Black Braided Drop Hose $\,$ - $S\Omega$ 3058 5

Water Hose		
PVC MD Clear White Helix Suction Hose	3070	18
PVC MD Green Suction Hose	3071	18
PVC HD Sub-Zero Suction Hose	3074	17
PVC HD Clear Braided Suction Hose	3076	15
EPDM Suction & Transfer Hose	3080	16

Accessories		
Banding Coils	3098	21
Banding Sleeves	3099	21

Couplings & Accessories		
Male Adapter x Female Thread	А	22
Female Coupler x Male Thread	В	22
Female Coupler x Hose Shank	С	23
Female Coupler x Female Thread	D	23
Male Adapter x Hose Shank	E	23
Male Adapter x Male Thread	F	24
Anti-Leak Aluminum C x E Cam Lock Couplings	ALF	25
Dust Cap	DC	24
Dust Plug	DP	24
Dust Cap w/Lock Out Handles	DCL	25
Tank Truck API Adapters, Caps & Couplers	DC, DA, DD, G	26
Vapor Recovery Couplers - Type C, Type C Crimp Fitting	С	27
Vapor Recovery Couplers - Type D, Type DA	D, DA	28
Pin Lug Couplings - Aluminum With Brass Swivel	AB	29
Pin Lug Couplings - Replacement Washers	HW	29
Spiral Double Bolt	SDB	30
Nipples - Combination & Victaulic	CN	30



THERMOPLASTIC HOSE SOLUTIONS

3058 NBR/PVC Black Braided Drop Hose



NBR/PVC tube, smooth bore with embedded SΩ ground wire in the hose wall with a sturdy clockwise PVC helix, one braid of high tensile polyester yarn reinforcement. Used to deliver gasoline, diesel fuel, kerosene and fuels with aromatic content to 40%.

3040 PU Clear Braided Drop Hose



Polyurethane tube, smooth bore with embedded SΩ ground wire in the hose wall with a sturdy clockwise PVC helix, one braid of high tensile polyester yarn reinforcement. Used in the delivery of biofuels, gasoline, kerosene and fuel oil.

3045 PU Black Braided Drop Hose



Polyurethane tube, smooth bore with embedded $S\Omega$ ground wire in the hose wall with a sturdy clockwise PVC helix, one braid of high tensile polyester yarn reinforcement. Used in the delivery of biofuels, gasoline, kerosene and fuel oil.

3050 PU Standard Clear Vapor Recovery Hose



Polyurethane tube with a sturdy clockwise PVC helix with $S\Omega$ ground wire embedded into the hose helix. Used to remove vapors from gasoline and alternative fuels to recovery system in tank truck operations.

3053 PU HD Clear Vapor Recovery Hose




Polyurethane tube with a sturdy clockwise PVC helix with $S\Omega$ ground wire embedded into the hose helix. Used to remove vapors from gasoline and alternative fuels to recovery system in tank truck and terminal operations.

3020 PU Lined PVC Material Handling Hose




Polyurethane abrasion resistant liner with a PVC cover and a sturdy clockwise PVC helix. For vacuum and transfer of abrasive crushed rock, gravel, sand or dry fertilizers, fly ash and also used for shot blast recovery.

3021 PU Duct and Material Handling Hose



Polyurethane abrasion resistant tube with sturdy clockwise PVC helix. For insulation blowing, fume removal, ducting, ventilation and dust collection.

3022 PU MD Material Handling Hose



Medium duty abrasion resistant polyurethane liner with static dissipating PVC cover and sturdy clockwise PVC helix. For dust collection, dry fertilizer, plastic pellets or any dry medium abrasive requirements.

THERMOPLASTIC HOSE SOLUTIONS



3030 PVC Mulch Hose




Abrasion resistant PVC tube with sturdy clockwise PVC helix. Standard duty material handling hose to dispense mulch, bark, wood chips or for resurfacing and landscaping.

3035 SBR Black Material Handling Hose



Abrasion resistant SBR tube and cover that are both static dissipating. Abrasive suction for crushed rock, sand, dry fertilizer, small gravel and powdered cement. Can also be used as a boom hose for catch basin clean out.

3076 PVC HD Clear Braided Suction Hose



PVC tube and sturdy clockwise PVC helix with high tensile strength polyester yarn reinforcement. For HD fish suction and transfer. Also HD water suction and transfer for rental, construction and trash pumps.

3080 EPDM Suction Hose



EPDM tube with polyurethane clockwise helix. For septic, waste water and liquid manure handling; agricultural liquid fertilizers and standard duty water suction, as well as suction and transfer for rental, construction and trash pumps.

3074 PVC HD Sub-Zero Suction Hose



PVC tube and sturdy clockwise PVC helix. For heavy duty water suction and transfer from rental, construction and trash pumps in subzero weather conditions.

3070 MD Clear White Helix Suction Hose **3071** MD Green Suction Hose



PVC tube and sturdy clockwise PVC helix. For standard medium duty water suction for rental, construction and trash pumps in construction and equipment rental.

3000 PVC FDA USDA Clear Braided Material Handling Hose



Polyurethane tube with high tensile strength polyester yarn reinforcement. Clockwise PVC helix with SΩ ground wire. For heavy duty food grade material handling, railcar unloading, abrasive suction and transfer.

3010 PVC FDA USDA 3A Clear Suction Hose



PVC tube and sturdy clockwise PVC helix. For transfer of food grade liquids, such as juices, wine, beer and potable water and dairy products.



APPLICATIONS GUIDE

	FO	OD	МА	TERI	AL HA	NDLI	NG		PET	ROLE	UM		WATER				
APPLICATIONS	3000	3010	3020	3021	3022	3030	3035	3040	3045			3058	3070	3071	3074	3076	3080
Fabric Reinforced	х							х	х			х				х	
With Ground Wire	х							х	х	х	х	х			х		
Clear Visual Flow	х	х		х	х	х		х		х	х		x		х	х	
Go Glide External Helix			х	х				х	х	х	х	х				х	х
Cold Temp to -40°F				х	х	х		Х	х	х	х				х		х
Abrasive Chute	х			х													
Animal Fat												Х					
Bilge Discharge													х	х			х
Biofuel Drop								х	х								
Compost, Seed Transfer						х											
Crushed Gravel Vacuum	х		х														
Dust Collection			х	х	х												
Fertilizer - Dry			х		х												
Fertilizer - Liquid													х	х			х
Fish Suction															х	х	
Fly Ash Collection				х													
Gasoline Drop								х				Х					
Gasoline Vapor Recovery										х							
Gold Dredge															х		
Ice Loading		х															
Industrial Vacuum			х														
Insulation Blowing				х													
Liquid Drain Line													х	х			
Liquid Food		х															
Liquid Manure																	х
Material Handling Basic			х	х	х												
Material Handling HD	х		х		х												
Milk Transfer		х															
Mulch, Bark, Wood Chips						х											
Poultry Processing	Ī	х															
Seeder Lines													х	х			
Shot Blast Vacuum	х		х														
Truck & Railcar Unloading	Х																
Water Suction HD	Ī														х	х	
Water Suction Standard													Х	х		х	









CONSTRUCTION: NBR/PVC tube, smooth bore with embedded S Ω ground wire in the hose wall with a sturdy clockwise PVC helix, one braid of high tensile polyester yarn reinforcement.

TEMPERATURE RANGE: -10°F (-23°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Used to deliver gasoline, diesel fuel, kerosene and fuels with aromatic content to 40%.

FEATURES:

- Higher transfer pressures.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- SΩ ground wire embedded into hose wall to help prevent the build-up of static electricity. Wire must be secured to ground to dissipate static electricity.

Part		I.D.	O.D.		Rein.	Max W.P. @68°F		Vacuum	Weight		Min. Bend Radius	
Number	in.	mm.	in.	mm.	Braids	PSI	BAR	@68°F	lb./ft.	KG/m	in.	mm
3058-0200-100	2	50.80	2.68	68.07	1	70	4.83	29.9	1.13	1.68	5.0	127.0
3058-0300-100	3	76.20	3.68	93.47	1	65	4.48	29.9	1.37	2.04	6.0	152.4
3058-0400-100	4	101.60	4.80	121.92	1	65	4.48	29.9	2.16	3.21	8.0	203.2

Note: Use JASON ORANGE banding sleeves only when securing coupling for 3" and 4" ID's.

Discharge pressures and vacuum are temperature dependent.

 $S\Omega$ = Safety Ohm



3040 POLYURETHANE DROP HOSE FOR SUCTION AND DELIVERY OF GASOLINE AND ALTERNATIVE FUELS - $S\Omega$









CONSTRUCTION: Polyurethane tube, smooth bore with embedded SΩ ground wire in the hose wall with a sturdy clockwise PVC helix, one braid of high tensile polyester yarn reinforcement.

TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Used in the delivery of biofuels, gasoline, kerosene and fuel oil.

FEATURES:

- Higher transfer pressures.
- Clear visual flow.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- SΩ ground wire embedded into hose wall to help prevent the build-up of static electricity. SΩ wire must be secured to ground to dissipate static electricity.
- Vacuum up to 29" of Hg.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein. Braids	Max W. PSI	P. @68°F BAR		Wei lb./ft.		-	nd Radius mm
3040-0200-100	2	50.80	2.46	62.48	1	75	5.17	29.0	0.63	0.94	4.0	101.6
3040-0300-100	3	76.20	3.78	96.01	1	65	4.48	29.0	1.20	1.79	6.0	152.4
3040-0400-100	4	101.60	4.83	122.68	1	65	4.48	29.0	1.71	2.54	8.0	203.2

Note: Use JASON GREEN banding sleeves only when securing coupling for 3" and 4" ID's. Discharge pressures and vacuum are temperature dependent.

 $S\Omega$ = Safety Ohm



3045 POLYURETHANE DROP HOSE FOR SUCTION AND DELIVERY OF GASOLINE AND ALTERNATIVE FUELS - $S\Omega$









CONSTRUCTION: Polyurethane tube, smooth bore with embedded $S\Omega$ ground wire in the hose wall with a sturdy clockwise PVC helix, one braid of high tensile polyester yarn reinforcement.

TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Used in the delivery of biofuels, gasoline, kerosene and fuel oil.

FEATURES:

- Higher transfer pressures.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- SΩ ground wire embedded into hose wall to help prevent the build-up of static electricity. SΩ wire must be secured to ground to dissipate static electricity.
- Vacuum up to 29" of Hg.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein. Braids	Max W.P. @68°F PSI BAR		Vacuum @68°F	Wei lb./ft.	Weight Ib./ft. KG/m		nd Radius mm
3045-0200-100	2	50.80	2.46	62.48	1	75	5.17	29.0	0.63	0.94	4.0	101.6
3045-0300-100	3	76.20	3.78	96.01	1	65	4.48	29.0	1.20	1.79	6.0	152.4
3045-0400-100	4	101.60	4.83	122.68	1	65	4.48	29.0	1.71	2.54	8.0	203.2

Note: Use JASON GREEN banding sleeves only when securing coupling for 3" and 4" ID's. Discharge pressures and vacuum are temperature dependent.


 $S\Omega$ = Safety Ohm








POLYURETHANE GASOLINE AND ALTERNATIVE FUEL VAPOR RECOVERY HOSE - S Ω









TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Used to remove vapors from gasoline and alternative fuels to recovery system in tank truck operations.

FEATURES:

- Clear visual flow.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- SΩ ground wire embedded into hose wall to help prevent the build-up of static electricity. SΩ wire must be secured to ground to dissipate static electricity.


BRRRRR

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein.	Max W.P. @68°F PSI BAR				ght KG/m	-	nd Radius mm
3050-0200-100	2	50.80	2.45	62.23	PVC Helix	10	0.69	15.0	0.50	0.74	3.0	76.2
3050-0300-100	3	76.20	3.54	89.92	PVC Helix	8	0.55	15.0	0.79	1.18	4.0	101.6
3050-0400-100	4	101.60	4.57	116.08	PVC Helix	7	0.48	12.0	1.11	1.65	5.0	127.0

Note: Use JASON YELLOW banding sleeves only when securing coupling for 2", 3" and 4" ID's. $S\Omega$ = Safety Ohm



3053 HD POLYURETHANE GASOLINE AND ALTERNATIVE FUEL VAPOR RECOVERY HOSE - SΩ







TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Used to remove vapors from gasoline and alternative fuels to recovery system in tank truck and terminal operations.

FEATURES:

- Clear visual flow.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- SΩ ground wire embedded into hose wall to help prevent the build-up of static electricity. SΩ wire must be secured to ground to dissipate static electricity.

BRRRRR Factor

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein.	Max W PSI	.P. @68°F BAR	Vacuum @68°F	Wei Ib./ft.	•		nd Radius mm
3053-0300-100 3053-0400-100	3 4	76.20 101.60	3.57 4.61		PVC Helix PVC Helix	-	0.55 0.48	15.0 12.0	0.95 1.27	1.41 1.89	5.0 6.0	127.0 152.4

Note: Use JASON YELLOW banding sleeves only when securing coupling for 3" and 4" ID's. S Ω = Safety Ohm




3020

HD POLYURETHANE LINED, PVC MATERIAL HANDLING HOSE







TEMPERATURE RANGE: -40°F (-40°C) to

+140°F (+60°C)

and also used for shot blast recovery.

 STANDARD LENGTHS: 1-1/2" to 6" - 100 ft. 6" and 8" - 20 ft. and 50 ft.
 APPLICATION: For vacuum and transfer of abrasive crushed rock, gravel, sand or dry fertilizers, fly ash

- FEATURES:
 - Abrasion resistant PU liner.
 - Static dissipating cover compound.
 - \bullet -40°F cold weather resistance.
 - Sub-zero flexibility.
 - Easy to drag with "Go-Glide" external clockwise PVC helix.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein.	Max W. PSI	P. @68°F BAR		Wei lb./ft.	•		end Radius mm
)	-	-		
3020-0150-100	1-1/2	2 38.10	1.85	46.99	PVC Helix	50	3.45	29.0	0.42	0.63	2.0	50.8
3020-0200-100	2	50.80	2.40	60.96	PVC Helix	40	2.76	29.0	0.59	0.88	3.0	76.2
3020-0250-100	2-1/2	2 63.50	3.09	78.49	PVC Helix	40	2.76	29.0	0.82	1.22	3.0	76.2
3020-0300-100	3	76.20	3.64	92.46	PVC Helix	40	2.76	29.0	1.18	1.76	4.0	101.6
3020-0400-100	4	101.60	4.76	120.90	PVC Helix	35	2.41	29.0	1.94	2.89	6.0	152.4
3020-0600-020	6	152.40	6.80	172.72	PVC Helix	30	2.07	28.0	3.50	5.21	12.0	304.8
3020-0600-050	6	152.40	6.80	172.72	PVC Helix	30	2.07	28.0	3.50	5.21	12.0	304.8
3020-0600-100	6	152.40	6.80	172.72	PVC Helix	30	2.07	28.0	3.50	5.21	12.0	304.8
3020-0800-020	8	203.20	9.16	232.66	PVC Helix	30	2.07	28.0	5.90	8.78	18.0	457.2
3020-0800-050	8	203.20	9.16	232.66	PVC Helix	30	2.07	28.0	5.90	8.78	18.0	457.2



3021


POLYURETHANE MATERIAL HANDLING AND DUCT HOSE





3022

MEDIUM DUTY POLYURETHANE LINED MATERIAL HANDLING HOSE









BRRRR FACTOR Down to -40°F

CONSTRUCTION: Medium duty abrasion resistant polyurethane liner with static dissipating PVC cover and sturdy clockwise PVC helix.

TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths **APPLICATION:** Dust collection, dry fertilizer, plastic pellets or any dry medium abrasive requirements.

FEATURES:

- Abrasion resistant PU tube.
- Clear visual flow.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- Static dissipating PVC cover compound.

Part Number									D.D. mm.	Rein.	Max W.P PSI	P. @68°F BAR		Weig Ib./ft.	ght KG/m	-	nd Radius mm
3022-0150-100	1-1/2	38.10	1.91	48.51	PVC Helix	30	2.07	24.0	0.29	0.43	1.37	34.8					
3022-0200-100	2	50.80	2.46	62.48	PVC Helix	25	1.72	22.0	0.40	0.60	2.50	63.5					
3022-0250-100	2-1/2	63.50	2.90	73.66	PVC Helix	20	1.38	19.0	0.54	0.80	2.50	63.5					
3022-0300-100	3	76.20	3.53	89.66	PVC Helix	20	1.38	18.0	0.68	1.01	4.00	101.6					
3022-0400-100	4	101.60	4.57	116.08	PVC Helix	15	1.03	13.0	1.01	1.50	6.00	152.4					



3030

PVC MULCH RESURFACING HOSE



sturdy clockwise PVC helix. **TEMPERATURE RANGE:** -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Standard duty material handling hose to dispense mulch, bark, wood chips or for resurfacing and landscaping.

- Abrasion resistant PVC tube.
- Clear visual flow.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.

Part Number	in.	I.D. mm.	c in.).D. mm.	Rein.	Max W. PSI	.P. @68°F BAR		Wei lb./ft.		-	nd Radius mm
)	-	-		
3030-0400-100	4	101.60			PVC Helix		2.41	29.0	1.35	2.01	9.0	228.6
3030-0500-100	5		5.60		PVC Helix	30	2.07	24.0	1.75	2.60	10.0	254.0
3030-0600-100	6	152.40	6.79	172.47	PVC Helix	25	1.72	24.0	2.42	3.60	11.0	279.4



3035

ABRASION RESISTANT SBR MATERIAL HANDLING HOSE







BRRRR FACTOR Down to -40°F

CONSTRUCTION: Abrasion resistant SBR tube and cover that are both static dissipating with a sturdy clockwise helix.

TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: All sizes - 100 ft.; 6" - 50 ft.

APPLICATION: Abrasive suction for crushed rock, sand, dry fertilizer, small gravel and powdered cement. Can also be used as a boom hose for catch basin clean out.

FEATURES:


- Heavy-duty abrasion resistance.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- No ground wire is needed as the tube and cover compound are static dissipating.
- Lightweight

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein.	Max W.I PSI	P. @68°F BAR		Wei lb./ft.	ght KG/m	_	nd Radius mm
3035-0150-100	1-1/2	2 38.10	1.82	46.23	PVC Helix	45	3.10	29.0	0.37	0.55	2.0	50.8
3035-0200-100	2	50.80	2.35	59.69	PVC Helix	40	2.76	29.0	0.50	0.74	2.5	63.5
3035-0250-100	2-1/2	2 63.50	2.95	74.93	PVC Helix	35	2.41	29.0	0.88	1.31	2.5	63.5
3035-0300-100	3	76.20	3.51	89.15	PVC Helix	35	2.41	29.0	1.10	1.64	3.0	76.2
3035-0400-100	4	101.60	4.63	117.60	PVC Helix	30	2.07	29.0	1.76	2.62	4.5	114.3
3035-0500-100	5	127.00	5.75	146.05	PVC Helix	30	2.07	28.0	2.47	3.68	5.0	127.0
3035-0600-050	6	152.40	6.73	170.94	PVC Helix	30	2.07	28.0	3.09	4.60	9.0	228.6
3035-0600-100	6	152.40	6.73	170.94	PVC Helix	30	2.07	28.0	3.09	4.60	9.0	228.6





3076 HEAVY-DUTY PVC SUCTION & TRANSFER HOSE



CONSTRUCTION: PVC tube and sturdy clockwise PVC helix with high tensile strength polyester yarn reinforcement.

TEMPERATURE RANGE: -13°F (-25°C) to +140°F (+60°C)

STANDARD LENGTHS: 1-1/2" to 6" - 100 ft. 6", 8" and 10" - 20 ft.

APPLICATION: HD fish suction and transfer. Also HD water suction and transfer for rental, construction and trash pumps.

- Clear visual flow.
- Higher transfer pressures.
- Excellent flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- Vacuum up to 29" of Hg.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein. Braids	Max W.I PSI	P. @68°F BAR			ight KG/m		nd Radius mm
3076-0150-100	1-1/2	38.10	2.03	51.56	1	110	7.58	29.0	0.47	0.70	2.5	63.5
3076-0200-100	2	50.80	2.60	66.04	1	100	6.89	29.0	0.69	1.03	4.0	101.6
3076-0250-100	2-1/2	63.50	3.01	76.45	1	100	6.89	29.0	0.74	1.10	5.0	127.0
3076-0300-100	3	76.20	3.70	93.98	1	100	6.89	28.0	1.13	1.68	6.0	152.4
3076-0400-100	4	101.60	4.78	121.41	1	80	5.52	28.0	1.74	2.59	7.0	177.8
3076-0600-020	6	152.40	7.17	182.12	1	70	4.83	28.0	2.99	4.45	9.0	228.6
3076-0600-100	6	152.40	7.17	182.12	1	70	4.83	28.0	3.88	5.77	10.0	254.0
3076-0800-020	8	203.20	9.34	237.24	1	60	4.14	28.0	5.55	8.26	16.0	406.4
3076-1000-020	10	254.00	11.63	295.40	1	40	2.76	28.0	8.90	13.24	25.0	635.0

Note: Discharge pressures and vacuum are temperature dependent.



WATER

EPDM SUCTION HOSE





FACTOR





CONSTRUCTION: EPDM tube with polyethylene clockwise helix.

TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Septic, waste water and liquid manure handling; agricultural liquid fertilizers and standard duty water suction, as well as suction and transfer for rental, construction and trash pumps.

FEATURES:

- Mild EPDM chemical resistance.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Clockwise polyethylene helix.
- Vacuum up to 29" of Hg.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein.	Max W.I PSI	P. @68°F BAR		Wei lb./ft.	•	-	nd Radius mm
3080-0150-100	1-1/2	2 38.10	1.85	46.99	PE Helix	50	3.45	29.0	0.41	0.61	3.8	96.5
3080-0200-100	2	50.80	2.43	61.72	PE Helix	50	3.45	29.0	0.67	1.00	5.5	139.7
3080-0300-100	3	76.20	3.52	89.41	PE Helix	45	3.10	29.0	1.10	1.64	7.5	190.5
3080-0400-100	4	101.60	4.60	116.84	PE Helix	38	2.62	29.0	1.84	2.74	11.5	292.1


Note: Vacuum is temperature dependent.

16

WATER



3074 HD SUB-ZERO COLD WEATHER CLEAR PVC SUCTION HOSE





'OR



CONSTRUCTION: PVC tube with sturdy clockwise PVC helix.

TEMPERATURE RANGE: -40°F (-40°C) to +140°F (+60°C)

STANDARD LENGTHS: 1-1/2" to 6" - 100 ft. 6", 8" and 10" - 20 ft.

APPLICATION: Heavy duty water suction and transfer for rental, construction and trash pumps in sub-zero weather conditions.

FEATURES:

- Clear visual flow.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.

Note: Vacuum is temperature dependent.

• Vacuum up to 29" of Hg.


Part		I.D.	(D.D.	Rein.	Max W	.P. @68°F	Vacuum	Wei	ght	Min. Be	end Radius
Number	in.	mm.	in.	mm.		PSI	BAR	@68°F	lb./ft.	KG/m	in.	mm
3074-0100-100	1	25.40	1.22	30.99	PVC Helix	43	2.97	29.0	0.15	0.22	2.0	50.8
3074-0125-100	1-1/4	31.75	1.48	37.59	PVC Helix	36	2.48	29.0	0.18	0.27	2.5	63.5
3074-0150-100	1-1/2	2 38.10	1.82	46.23	PVC Helix	36	2.48	29.0	0.28	0.42	2.5	63.5
3074-0200-100	2	50.80	2.35	59.69	PVC Helix	36	2.48	29.0	0.44	0.65	3.0	76.2
3074-0250-100	2-1/2	2 63.50	2.87	72.90	PVC Helix	28	1.93	29.0	0.60	0.89	5.0	127.0
3074-0300-100	3	76.20	3.50	88.90	PVC Helix	28	1.93	29.0	0.85	1.26	6.0	152.4
3074-0400-100	4	101.60	4.63	117.60	PVC Helix	21	1.45	29.0	1.34	1.99	9.0	228.6
3074-0500-100	5	127.00	5.63	143.00	PVC Helix	21	1.45	28.0	2.20	3.27	10.0	254.0
3074-0600-020	6	152.40	6.73	170.94	PVC Helix	21	1.45	28.0	2.72	4.05	11.0	279.4
3074-0600-100	6	152.40	6.73	170.94	PVC Helix	21	1.45	28.0	2.72	4.05	11.0	279.4
3074-0800-020	8	203.20	9.04	229.62	PVC Helix	21	1.45	28.0	4.84	7.20	16.0	406.4
3074-1000-100	10	254.00	11.18	283.97	PVC Helix	14	0.97	28.0	7.06	10.51	30.0	762.0
3074-1200-020	12	304.80	13.30	337.82	PVC Helix	14	0.97	26.0	9.74	14.49	40.0	1016.0

WAITER HOSE



WATER

3070 MED. DUTY PVC SUCTION HOSE, CLEAR W/ WHITE HELIX **3071** MED. DUTY PVC SUCTION HOSE, GREEN W/ GREEN HELIX





CONSTRUCTION: PVC tube with a sturdy clockwise PVC helix.

TEMPERATURE RANGE: -5°F (-21°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Standard medium duty water suction for rental, construction and trash pumps in construction or equipment rental.

EATURES:	
----------	--

- Series 3070 with clear visual flow.
- Vacuum up to 29" of Hg.

Note: Vacuum is temperature dependent.

		· · ·								
Part Number	I.D. in. mm.	O.D. in. mm.	Rein.	Max W.P. PSI	@68°F BAR	Vacuum @68°F	Weig lb./ft.		_	nd Radius mm
3070-0100-100 3070-0125-100 3070-0150-100 3070-0200-100 3070-0250-100 3070-0300-100 3070-0400-100 3070-0600-100	1 25.40 1-1/4 31.75 1-1/2 38.10 2 50.80 2-1/2 63.50 3 76.20 4 101.60 6 152.40	1.4637.081.7243.692.2857.912.8371.883.3585.094.45113.03	PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix	85 64 57 50 50 50	5.86 5.86 4.41 3.93 3.45 3.45 3.45 3.45 1.45	29.0 29.0 29.0 29.0 29.0 29.0 29.0 29.0	0.18 0.24 0.33 0.55 0.79 0.97 1.71 3.65	0.27 0.36 0.49 0.82 1.18 1.44 2.54 5.43	3.0 4.0 5.0 8.0 10.0 12.0 14.0 25.0	76.2 101.6 127.0 203.2 254.0 304.8 355.6 635.0
3071-0100-100 3071-0125-100 3071-0150-100 3071-0250-100 3071-0250-100 3071-0300-100 3071-0400-100 3071-0600-100	1 25.40 1-1/4 31.75 1-1/2 38.10 2 50.80 2-1/2 63.50 3 76.20 4 101.60 6 152.40	1.18 29.97 1.46 37.08 1.72 43.69 2.28 57.91 2.83 71.88 3.35 85.09 4.45 113.03	PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix PVC Helix	85 85 64 57 50 50 50	5.86 5.86 4.41 3.93 3.45 3.45 3.45 1.45	29.0 29.0 29.0 29.0 29.0 29.0 29.0 29.0	0.18 0.24 0.33 0.55 0.79 0.97 1.71 3.65	0.27 0.36 0.49 0.82 1.18 1.44 2.54 5.43	3.0 4.0 5.0 8.0 10.0 12.0 14.0 25.0	76.2 101.6 127.0 203.2 254.0 304.8 355.6 635.0

18

FOOD




3000

POLYURETHANE FDA USDA MATERIAL HANDLING HOSE - S Ω











CONSTRUCTION: Polyurethane tube with high tensile strength polyester yarn reinforcement. Clockwise PVC helix with S Ω ground wire. **TEMPERATURE RANGE:** -40°F (-40°C) to

140°F (+60°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Heavy duty food grade material handling, railcar unloading, abrasive suction and transfer.

FEATURES:

- Meets FDA requirements.
- Approved by USDA for use in meat & poultry plants.
- Clear visual flow.
- Higher transfer pressures.
- Safety Ohm $(S\Omega)$ ground wire embedded into the hose wall to help prevent the build-up of static electricity. S Ω wire must be secured to ground to dissipate static electricity.
- -40°F cold weather resistance.
- Sub-zero flexibility.
- Easy to drag with "Go-Glide" external clockwise PVC helix.
- Vacuum up to 29" of Hg.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein. Braid	Max W. PSI	P. @68°F BAR		Wei lb./ft.	ght KG/m	-	end Radius mm
3000-0300-100	3	76.2	3.80	96.5	1	70	4.83	29.0	1.20	1.79	4.0	101.6
3000-0400-100	4	101.6	4.85	123.2	1	65	4.48	29.0	1.60	2.38	6.0	152.4
3000-0500-100	5	127.0	5.80	147.3	1	45	3.10	28.0	2.46	3.66	10.0	254.0
3000-0600-100	6	152.4	6.92	175.8	1	40	2.76	28.0	2.86	4.26	12.0	304.8

Note: Vacuum and discharge pressures are temperature dependent.

 $S\Omega$ = Safety Ohm



FOOD

3010

HD PVC FDA USDA 3-A LIQUID FOOD SUCTION HOSE









CONSTRUCTION: PVC tube with a sturdy clockwise PVC helix.

TEMPERATURE RANGE: -5°F (-23°C) to +140°F (+60°C)

STANDARD LENGTHS: 100 ft. lengths

APPLICATION: Transfer of food grade liquids, such as juices, wine, beer and potable water and dairy products.

FEATURES:

- Meets FDA requirements.
- Approved by USDA for use in meat and poultry plants.
- Meets 3-A sanitary standards, which includes processing dairy products.
- Clear visual flow.
- Vacuum up to 29" of Hg.

Part Number	in.	I.D. mm.	in.	D.D. mm.	Rein.	Max W PSI	.P. @68°F BAR			ght KG/m		nd Radius mm
3010-0100-100	1	25.40	1.24	31.50	PVC Helix	71	4.90	29.9	0.26	0.39	3.0	76.2
3010-0125-100	1-1/4	31.75	1.54	39.12	PVC Helix	64	4.41	29.9	0.34	0.51	4.0	101.6
3010-0150-100	1-1/2	38.10	1.82	46.23	PVC Helix	57	3.93	29.9	0.44	0.65	6.0	152.4
3010-0200-100	2	50.80	2.39	60.71	PVC Helix	57	3.93	29.9	0.74	1.10	8.0	203.2
3010-0250-100	2-1/2	63.50	2.93	74.42	PVC Helix	57	3.93	29.9	1.01	1.50	10.0	254.0
3010-0300-100	3	76.20	3.43	87.12	PVC Helix	57	3.93	29.9	1.21	1.80	12.0	304.8
3010-0400-100	4	101.60	4.53	115.06	PVC Helix	43	2.97	29.9	2.02	3.01	15.0	381.0


Note: Vacuum and discharge pressures are temperature dependent.

ACCESSORIES



BANDING COILS

3098



CONSTRUCTION: Clear FDA PVC.

APPLICATION: Clockwise coils allow for a better coupling securing surface on the hose O.D.

FEATURES:


- Made with clear FDA PVC, 3098 can be used on any thermoplastic cover compound.
- Fits high profile clockwise O.D. corrugations for a smooth coupling securing surface.
- Fits low profile clockwise O.D. corrugations for a slightly raised coupling securing surface.
- Cut one length in half to accomodate both ends of one hose assembly.

Part	Fits I	Hose ID	Coil	Length
Number	in.	mm.	in.	mm.
3098-0150	1-1/2	38.1	6	152.4
3098-0200	2	50.8	7	177.8
3098-0250	2-1/2	63.5	8	203.2
3098-0300	3	76.2	8	203.2
3098-0400	4	101.6	9	228.6
3098-0500	5	127.0	10	254.0
3098-0600	6	152.4	14	355.6

3099



Cut to 12" sleeves for each end of the assembly.







BANDING SLEEVES

CONSTRUCTION: Green, yellow or orange PVC

APPLICATION: Banding sleeves are made to thread over the outside of Jason thermoplastic petroleum hoses to allow better coupling securing surface on the O.D. of the hose.

FEATURES:

- Color-coded to fit specific Jason petroleum hoses
- Clockwise threading
- All sleeve lengths are 3 ft.

Part	Fits	Hose ID	Use On	Sleeve
Number	in.	mm.	Hose Series	Color
3099-03-3040	3	76.2	3040	Green
3099-04-3040	4	101.6	3040	Green
3099-03-3045	3	76.2	3045	Green
3099-04-3045	4	101.6	3045	Green
3099-02-3050	2	50.8	3050	Yellow
3099-03-3050	3	76.2	3050	Yellow
3099-04-3050	4	101.6	3050	Yellow
3099-03-3053	3	76.2	3053	Yellow
3099-04-3053	4	101.6	3053	Yellow
3099-03-3058	3	76.2	3058	Orange
3099-04-3058	4	101.6	3058	Orange



Separate parts provide unique, quick coupling hose connections for liquids or solids. All parts (3/4" to 6", not including the 5" ID) are manufactured to comply with MIL Spec A-A-59326A. They will interchange with couplings manufactured to the same standards (excluding 1/2" and 8"). Female couplers are supplied with safety pins. Cam arms are 304 stainless steel. 5" parts are made to ASTM specifications. Anodized hardcoat couplings are available. Contact Jason Customer Service for details.

Working Pressures (maximum PSI) for Cam and Groove Couplers and Adapters

Size	Aluminum	Stainless Steel	Brass	Polypropylene
1/2		150		125
3⁄4	250	250	250	125
1	250	250	250	125
1-1/4	250	250	250	100
1-1/2	250	250	250	100
2	250	250	250	100
2-1/2	150	150	150	
3	125	125	125	75
4	100	100	100	60
5	75	75	75	
6	75	75	75	
8	50	50	50	

 Metal coupling pressures are based on ambient temperature (+70°F or +21°C) with standard NBR gasket.

 Plastic coupling pressures are based on ambient temperature (+70°F or +21°C) with standard NBR gasket.

PART A MALE ADAPTER x FEMALE THREAD

Male end fits coupler or Dust Cap. Female thread end is NPT.

		Black SCH.80				
	Size	Aluminum	304 Stainless	316 Stainless	Brass	Polypropylene
	1/2		A050S	A050SS		A050P
1000	3/4	A075A	A075S	A075SS	A075B	A075P
	1	A100A	A100S	A100SS	A100B	A100P
	1-1/4	A125A	A125S	A125SS	A125B	A125P
	1-1/2	A150A	A150S	A150SS	A150B	A150P
	Ź	A200A	A200S	A200SS	A200B	A200P
	2-1/2	A250A	A250S	A250SS	A250B	
1008	3	A300A	A300S	A300SS	A300B	A300P
	4	A400A	A400S	A400SS	A400B	A400P
	5	A500A				
	6	A600A	A600S	A600SS	A600B	
	8	A800A**				
	8	A801A**				

PART BFEMALE COUPLER x MALE THREAD

Female end fits male adapter or Dust Plug. Male end thread is NPT. Bowl has recess for washer replacement.

			PART	NUMBER		Black SCH.80
	Size	Aluminum	304 Stainless	316 Stainless	Brass	Polypropylene
	1/2 3/4	B075A	B050S B075S	B050SS B075SS	B075B	B050P B075P
	1 1-1/4	B100A B125A	B100S B125S	B100SS B125SS	B100B B125B	B100P B125P
	1-1/2	B150A	B150S	B150SS	B150B	B150P
	2 2-1/2	B200A B250A	B200S B250S	B200SS B250SS	B200B B250B	B200P
Real Providence	3	B300A B400A	B300S B400S	B300SS B400SS	B300B B400B	B300P B400P
W.	5	B500A				DTOOL
	6 8	B600A B800A**	B600S	B600SS	B600B	
	8	B801A**				

All sizes may not be stocked in all locations. Check with customer service for availability. **See Page 23 for interchange.



FEMALE COUPLER x HOSE SHANK

Female end fits male adapter or Dust Plug. Shank fits into hose ID. Bowl has recess for washer replacement.

DO NOT CRIMP WITH	Size	Aluminum	PART N 304 Stainless	IUMBER 316 Stainless	Brass	Black SCH.80 Polypropylene
FERRULES	1/2		C050S	C050SS		C050P
	3/4	C075A	C075S	C075SS	C075B	C075P
AND DO	1	C100A	C100S	C100SS	C100B	C100P
	1-1/4	C125A	C125S	C125SS	C125B	C125P
40 P	1-1/2	C150A	C150S	C150SS	C150B	C150P
	Ź	C200A	C200S	C200SS	C200B	C200P
	2-1/2	C250A	C250S	C250SS	C250B	
	3 [´]	C300A	C300S	C300SS	C300B	C300P
	4	C400A	C400S	C400SS	C400B	C400P
	5	C500A				
	6	C600A	C600S	C600SS	C600B	
	8	C800A**				
	8	C801A**				

PART D FEMALE COUPLER x FEMALE THREAD

Female end fits male adapter or Dust Plug. Female end thread is NPT. Bowl has recess for washer replacement.



PART C

		PART NUMBER					
Size	Aluminum	304 Stainless	316 Stainless	Brass	Polypropylene		
1/2		D050S	D050SS		D050P		
3⁄4	D075A	D075S	D075SS	D075B	D075P		
1	D100A	D100S	D100SS	D100B	D100P		
1-1/4	D125A	D125S	D125SS	D125B	D125P		
1-1/2	D150A	D150S	D150SS	D150B	D150P		
2	D200A	D200S	D200SS	D200B	D200P		
2-1/2	D250A	D250S	D250SS	D250B			
3	D300A	D300S	D300SS	D300B	D300P		
4	D400A	D400S	D400SS	D400B	D400P		
5	D500A						
6	D600A	D600S	D600SS	D600B			
8	D800A**						
8	D801A**						

PART E MALE ADAPTER x HOSE SHANK

Male end fits female coupler or Dust Cap. Shank fits into hose ID.

DO NOT CRIMP WITH	Size	Aluminum	PART N 304 Stainless	NUMBER	Brass	Black SCH.80 Polypropylene
FERRULES	5126	Alumnum	JU4 Stailless	510 Stalliess	Diass	Polypropylelle
	1/2		E050S	E050SS		E050P
	3/4	E075A	E075S	E075SS	E075B	E075P
	1	E100A	E100S	E100SS	E100B	E100P
ALC: 100	1-1/4	E125A	E125S	E125SS	E125B	E125P
	1-1/2	E150A	E150S	E150SS	E150B	E150P
0	2	E200A	E200S	E200SS	E200B	E200P
- ESDA	2-1/2	E250A	E250S	E250SS	E250B	
A CONTRACTOR OF A CONTRACTOR OFTA CONTRACTOR O	3	E300A	E300S	E300SS	E300B	E300P
	4	E400A	E400S	E400SS	E400B	E400P
	5	E500A				
	6	E600A	E600S	E600SS	E600B	
	8	E800A**				
	8	F801A**				

All sizes may not be stocked in all locations. Check with customer service for availability. **See Page 23 for interchange. We disclaim any liability for use of our products in applications other than which they are designed.



MALE ADAPTER x MALE THREAD

Male end fits female coupler or Dust Cap. Male end thread is NPT.

Size	Aluminum		NUMBER 316 Stainless	Brass	Black SCH.80 Polypropylene
1/2 3/4 1 1-1/4 1-1/2 2 2-1/2 3 4 5 6 8 8	F075A F100A F125A F150A F200A F250A F300A F400A F500A F600A F800A** F801A**	F050S F075S F100S F125S F150S F200S F250S F300S F400S F600S	F050SS F075SS F100SS F125SS F150SS F200SS F250SS F300SS F400SS F600SS	F075B F100B F125B F150B F200B F250B F300B F400B F600B	F050P F075P F100P F125P F150P F200P F300P F400P

PART DC

DUST CAP

Fits male adapters.

PART F




Size	Aluminum		NUMBER 316 Stainless	Brass	Black SCH.80 Polypropylene
1/2		DC050S	DC050SS		DC050P
3/4	DC075A	DC075S	DC075SS	DC075B	DC075P
1	DC100A	DC100S	DC100SS	DC100B	DC100P
1-1/4	DC125A	DC125S	DC125SS	DC125B	DC125P
1-1/2	DC150A	DC150S	DC150SS	DC150B	DC150P
2	DC200A	DC200S	DC200SS	DC200B	DC200P
2-1/2	DC250A	DC250S	DC250SS	DC250B	
3	DC300A	DC300S	DC300SS	DC300B	DC300P
4	DC400A	DC400S	DC400SS	DC400B	DC400P
5	DC500A				
6	DC600A	DC600S	DC600SS	DC600B	
8	DC800A**				
8	DC801A**				

PART DP

DUST PLUG

Fits male adapters.



All sizes may not be stocked in all locations. Check with customer service for availability. **See Page 23 for interchange.

We disclaim any liability for use of our products in applications other than which they are designed.

24



COUPLINGS

SERIES 800 & SERIES 801 8" CAM & GROOVE INTERCHANGE


There has always been a problem with interchangeability with 8" cam and groove couplings. Jason now introduces the **801 SERIES** in addition to the current line to solve that problem. Below you will see how the **800** and **801** Series match up:

800 Series Interchanges with: PT Domestic, Kuriyama of America					
Jason Part Numbers					
A800A	E800A				
B800A	F800A				
C800A	DC800A				
D800A	DP800A				

801 Series Int Dixon Andrews, N PT		
Jason Pa		
A801A	E801A	*Check with
*B801A	*F801A	customer service for
C801A	*DC801A	
D801A	*DP801A	availability.

ANTI-LEAK ALUMINUM C x E CAM-LOCK COUPLINGS

This new cam-lock employs a patented design that relies on two bands of rubber that act as a type of gasket surrounding two specific grooves on the cam-lock shank. When the hose wall is compressed against the bands of rubber, a preventive barrier is formed reducing the chance for leaks around the couplings.



REPLACEMENT BANDS - NITRILE						
ID	1-1/2″	2"	3"	4″	6″	
Part No.	RB15NBR	RB20NBR	RB30NBR	RB40NBR	RB60NBR	

PART DCL DUST CAP WITH LOCK OUT HANDLES

Handles fold over top of cap. Hole provided for padlock or seal. Padlock or seal not furnished.


		PART NUMBER			
	Size	Aluminum with SS Handles	Stainless Steel with SS Handles		
	1-1/2	DCL150A	DCL150S		
	2	DCL200A	DCL200S		
-6 H-1 C)	2-1/2	DCL250A	DCL250S		
	3	DCL300A	DCL300S		
	4	DCL400A	DCL400S		
	6	DCL600A	DCL600S		

All sizes may not be stocked in all locations. Check with customer service for availability. We disclaim any liability for use of our products in applications other than which they are designed.




TANK TRUCK API ADAPTERS, CAPS & COUPLERS


For offloading through the API adapter and coupler.



Size	Part No.	Description	Material
4"	DC400ATC	API Dust Cap	Aluminum
4"	DC400PPTC	API Dust Cap	Polypropylene



Size	Part No.	Description	Material
4" x 3"	DA4030ATC	4" API Coupler x 3" Adapter	Aluminum
4" x 4"	DA4040ATC	4" API Coupler x 4" Adapter	Aluminum



Size	Part No.	Description	Material
4" x 4"	DD4040ATC	4" API Coupler x 4" Coupler	Aluminum

Size	Part No.	Description	Material
4"	G400NBRTC	Gasket for 4" API Coupler	Nitrile

All sizes may not be stocked in all locations. Check with customer service for availability. We disclaim any liability for use of our products in applications other than which they are designed.

VAPOR RECOVERY COUPLER TYPE C FEMALE COUPLER x HOSE SHANK



Part No.	Size	Size Description
C4030AVP	4" x 3"	4" Coupler w/Probe x 3" Hose Shank
C300AVP	. 3"	3" CoupArting protogonx 3" Hose Shank
C400AVP	Size	4" Coupler w/Probe x 4" Hose Shank

Note: Do not crimp with ferrules.

For vapor recovery only. Not intended for liquid service.

EAGLElite INDUS


OWERING GLOBAL INDUSTRY

FAX: (86-7)-2 E-mail: EagleHQ(a)

FAX: (86-2)-2

VAPOR RECOVERY COUPLER - CRIMP FITTING^{il: EagleHQ@r} TYPE C FEMALE COUPLER x HOSE SHANK





Part No.	Size	Size Description
C4030AVPC	4" x 3"	4" Coupler w/Probe x 3" Hose Shank 3" Coup ໄ ຊ)
C300AVPC	. 3"	3" Coupled wy fingle av 3" Hose Shank
C400AVPC	Size	4" Coupler w/Probe x 4" Hose Shank

Note: For vapor recovery only. Not intended for liquid service.



CAM & GROOVE COUPLINGS Aluminum

VAPOR RECOVERY COUPLER TYPE DA FEMALE COUPLER X MALE ADAPTER



Ŕ				ST I	
	T	<u>lì í</u>	-1		
(a)					
			_)		
	4				

Part No.	Size	Size Description
DA4030AVP	4" x 3"	4" Coupler w/Probe x 3" Adapter


Note: For vapor recovery only. Not intended for liquid service.

EAGLElite INDUST

FAX: (86-2)-2: E-mail: EagleHQ@n

VAPOR RECOVERY COUPLER TYPE D FEMALE COUPLER x FEMALE THREAD





Part No.	Size	Size Description
D4030AVP	4" x 3"	4" Coupler w/Probe x 3" Female Thread (NPT)
D300AVP	3"	3" Coupler w/Proberx 3" Female Thread (NPT)
D400AVP	4" Si	Z€ Coupler w/Probe x 4" Female Thread (NPT)

Note: For vapor recovery only. Not intended for liquid service.

28

PIN LUG COUPLINGS



Threaded couplings for suction or discharge of water or other fluids. Standard threading is NPSM; National Pipe Straight Mechanical. 1-1/2" and 2-1/2" are available with additional NST thread; American National Fire Hose Straight Thread. (NST does not interchange). Pin lugs are on all sizes of female end. 2-1/2" through 6" have pin lugs on male end.

SET (M x F) PIN LUG SHANK COUPLINGS



Size	Thread	Aluminum W Brass Swivel
1-1/2	NPSM	AB150
1-1/2	NST	AB150NST
2	NPSM	AB200
2-1/2	NPSM	AB250
2-1/2	NST	AB250NST
3	NPSM	AB300
4	NPSM	AB400
6	NPSM	AB600

Iron Pin Lug Couplings available by special order.

FEMALE PIN LUG SHANK COUPLINGS

	Size	Thread	Aluminum W Brass Swivel
	1-1/2	NPSM	AB150
The second se	1-1/2	NST	AB150NST
	2	NPSM	AB200
	2-1/2	NPSM	AB250
	2-1/2	NST	AB250NST
	3	NPSM	AB300
	4	NPSM	AB400
	6	NPSM	AB600

REPLACEMENT WASHERS FOR PIN LUG SHANK COUPLINGS

COUPLING SIZE	1-1/2	1-1/2 NST	2	2-1/2	2-1/2 NST	3	4	6
PART NUMBER	HW150	HW150NST	HW200	HW250	HW250NST	HW300	HW400	HW/600



CLAMPS & NIPPLES

DOUBLE BOLT HOSE CLAMPS FOR CORRUGATED HOSE



Clamps (for corrugated hose) manufactured in either clockwise (right hand) or counter clockwise (left hand) design, the spiral double bolt clamp fits between the convolutions on corrugated hose. When fully tightened, the wire secures the full circumference of the outside hose wall - not the convolutions, for a safe, economical and efficient securing method. Consult hose manufacturer for correct convolution direction. Direction of clamp spiral and hose convolution are the same.

Hose ID	1-1/2	2	2-1/2	3	4
Part No*	SDB150	SDB200	SDB250	SDB300	SDB400
Hose ID Part No*	5 SDB500	6 SDB600	8 SDB800	10 SDB1000	12 SDB1200
*Specify clockwise -cw c			322000	3221000	3001200

COMBINATION HOSE NIPPLES



CN's are used in a variety of fluid applications. They are available in unplated steel, plated steel, polypropylene and 304 stainless steel. End (male) threads are NPT (will mate with foot valves, strainers, cam and groove part A, D etc.) and are the same size as shank.

Not for use with crimp ferrule.





POLYPROPYLENE

VICTAULIC

Hose ID	1/2	3/4	1	1-1/4	1-1/2	2	2-1/2
Part No	-7 -	-/ -	· · ·	, .			
Unplated	CN050	CN075	CN100	CN125	CN150	CN200	CN250
Plated	CN050P	CN075P	CN100P	CN125P	CN150P	CN200P	CN250P
304 Stainless	CN050S	CN075S	CN100S	CN125S	CN150S	CN200S	CN250S
Polypropylene*	CN050PP	CN075PP	CN100PP	CN125PP	CN150PP	CN200PP	CN250PP
Victaulic	CN050V	CN075V	CN100V	CN125V	CN150V	CN200V	CN250V
Hose ID	3	4	5	6	8	10	12
Part No							
Unplated	CN300	CN400	CN500	CN600	CN800	CN1000	CN1200
Plated	CN300P	CN400P	CN500P	CN600P	CN800P	CN1000P	CN1200P
304 Stainless	CN300S	CN400S		CN600S			
Polypropylene*	CN300PP	CN400PP					

*Black Schedule 80

All sizes may not be stocked in all locations. Check with customer service for availability.

CHEMICAL RESISTANCE TABLES PVC, EPDM & POLYURETHANE

POWERING GLOBAL INDUSTRY

WARNING: Responsibility for determining the suitability of any hose for any application rests with the user. Therefore, the user assumes all risks regarding any chemical or chemicals used in or around the hose. Neglecting to make this determination may result in hose failure, possible damage to property and or serious bodily injury. Jason disclaims any liability for use of our products in applications other than which they are designed.

1-EXCELLENT	2-GOOD	3-LIM	ITED	4-UN	SATISFAC	FORY
HOSE CONSTRUCTION WITH TEMPERATURE						
MATERIAL	PV0 68	C (F°) 104	EPDM (F°) 68 104		POLYURETHANE (F°) 68 104	
Acetaldehyde	4	4	4	4	4	4
Acetaldehyde 40%	4	4			4	4
Acetate solvents, crude	4	4			3	4
Acetate solvents, pure	4	4			3	4
Acetic Acid 0 -1%	1	2	1	1	4	4
Acetic Acid 20-30%	1	2	3	3	4	4
Acetic Acid 80%	2	2	4	4	4	4
Acetic Acid Vapors	1	2			4	4
Acetic Acid Glacial	2	3			4	4
Acetic Anhydride	4	4	4	4	4	4
Acetone	2	3	4	4	3	4
Acetylene	1	1			1	1
Acrylonitrite	1	2				
Adipic Acid	2	3			4	4
Allyl Alcohol 96%	4	4			4	4
Allyl Chloride	3	3	-		4	4
Alum	1	1	1	1	1	1
Aluminum Acetate	2	3 4				
Aluminum Alkyl	4	4			2	2
Aluminum Chloride Aluminum Flouride	1	1			3	3 1
Aluminum Hydroxide	1		1	1	2	3
Aluminum Nitrate	1	2		•	1	1
Aluminum Oxychloride	1	1				
Aluminum Phosphate Solution	4	4				
Aluminum Salts	1	1				
Aluminum Sulphate	1	1			1	1
Aminoethanol	2					
Ammonia - Aqueos	1				3	4
Ammonia - Dry Gas	3	4			3	4
Ammonia Liquid	4	4			3	4
Ammoniated Latex	1	3				
Ammonium Acetate	1	1				
Ammonium Bicarbonate	1	1				
Ammonium Carbonate	1	1			1	1
Ammonium Chloride Solution	1	1			2	3
Ammonium Flouride 25%	4	4			3	4
Ammonium Hydroxide (30% NH)	4	4	3	3	3	4
Ammonium Metaphosphate	1	1			2	2
Ammonium Nitrate	1	1			2	2
Ammonium Persulfate	1	1			2	2
Ammonium Phosphate Solutions	1	1				
Ammonium Sulfate	1	1				
Ammonium Sulfide	1	1	1	1	1	1
Ammonium Thiocyanate	1	1			2	2
Amyl Acetate	4	4				
Amyl Alcohol	1	2			4	4
Amyl Chloride	4	4				4
Aniline Aniline Chlorobydrate	2	3			4	4 4
Aniline Chlorohydrate	4	4 4			4 4	4
Aniline Hydrochloride Animal Gelatin	4	7	4	4	4	4
Animal Oil	1	1	4	4		



1-EXCELLENT

2-GOOD

3-LIMITED

HOSE CONSTRUCTION WITH TEMPERATURE

4-UNSATISFACTORY

Anthraquinone 1 1 1 Anthraquinonesufonic Acid 1 1 4 4 Antimory Chloride 1 1 1 1 1 Antimony Satts 1 1 1 1 1 Antimony Trichloride 1 1 1 1 1 Apple Juice 1							
Anthraguinore with a set of a se	MATERIAL						
Antireger Antireger Antireger Antireger Antireger11144Antireger Antireger Antireger11111Antireger Antireger11111Antireger Antireger11111Aqua Regia Aqua Regia344444Aqua Regia Annalt i Agriconthes33311 </td <td>Ant Oil</td> <td>4</td> <td>4</td> <td></td> <td></td> <td></td> <td></td>	Ant Oil	4	4				
Antimory ChronizeIIAntimory SaltsIIAntimory TrichorideIIIApple JuiceIIIApple JuiceIIIApple SaltsIIIApple Apple	Anthraquinone	1	1				
Antimory CharaceIIAntimory SinchardsIIIAntimory TrichlorideIIIApple JuiceIIIApua Regia34IApua Regia34IApua RegiaIIIApua RegiaIIIAnatile HydrosoftonsIIIArsenic Acid BONIIIIArsenic Acid BONIIIIArsenic Acid BONIIIIArsenic Acid BONIIIIArsenic TrichlorideIIIIArsenic TrichlorideI <td>Anthraquinonesufonic Acid</td> <td>1</td> <td>1</td> <td></td> <td></td> <td>4</td> <td>4</td>	Anthraquinonesufonic Acid	1	1			4	4
Antimory Salts1IIApple Juice11IApple Juice11IAppa Annonia44IAqua Annonia33IAnonati E hydrocarbons33IArsenic Aria Boh's12IIArsenic Aria Boh's12IIArsenic Aria Boh's11IIArsenic Aria Boh's33IIArsenic Trichloride11IIArsenic Aria Boh's34IIArsenic Aria Boh's34IIArsenic Trichloride1IIIArsenic Trichloride34IIArsenic Trichloride1IIIArsenic Trichloride34IIArsenic Trichloride1IIIArsenic Trichloride234IIArsenic Trichloride234IIArsenic Trichloride1IIIIArsenic Trichloride1IIIIArsenic Trichloride1IIIIArsenic Trichloride1IIIIArsenic Trichloride1IIIIArsenic Trichloride1IIIIArsenic TrichlorideII <t< td=""><td>Antifreeze</td><td>1</td><td>1</td><td></td><td></td><td></td><td></td></t<>	Antifreeze	1	1				
Antimory TrichlorideIIIApple JukeIIIAqua Angona44IAqua Angona33IAqua Angona33IAngona Compressed44IAngona Compressed33IArenic Acid 80%I2IIArenic Acid 80%I1IIArenic Acid 80%IIIIArenic Acid 80%IIII <td>Antimony Chloride</td> <td>1</td> <td></td> <td></td> <td></td> <td></td> <td></td>	Antimony Chloride	1					
Apple JureIIIIAqua Amnonia444Aqua Amnonia44Aqua Amnonia34444Aromatic Acid BON's33333Arsenic Acid BON's12111Arsenic Acid BON's33444Arsenic Acid BON's34441Arsenic Trichoride111444Asharel Transformer Oili)44411ASharel Di If I114411ASTM Fuel Oil If I114411ASTM Fuel Oil If I234411ASTM Fuel Oil If I114423ASTM Fuel Oil If I234411ASTM Fuel Oil If I111111ASTM Fuel Oil If I111111ASTM Fuel Oil If I1111111ASTM Fuel Oil If I1111111ASTM Fuel Oil If I1111111111111111111111111111111111 <td< td=""><td></td><td>-</td><td></td><td></td><td></td><td></td><td></td></td<>		-					
Aque Annonia44Aque Regio33Aque Regio33Aronatic Hydrocations33Arsenic Acid 60%1244Arsenic Acid 60%1111Arsenic Trichloride1111Arsenic Trichloride3444Arsenic Trichloride3444Arsenic Trichloride3444Arsenic Trichloride3441Arsenic Trichloride34411Arsenic Trichloride34411Arsenic Trichloride234411Arsenic Trichloride234411Arsenic Trichloride2344111Arst Fuel Ol #12244423Arst Fuel Ol #244442331Arst Fuel Ol #211<	-					1	1
Aque Regin3444Argen Compressed447Arsenic Acid 80%1244Arsenic Acid 80%1244Arsenic Acid 80%1244Arsenic Acid 80%1111Arsenic Acid 80%11144Arsenic Trichoride11444Asharel [Transformer Oil]44411ASTM Fuel Oil #1114411ASTM Fuel Oil #2234411ASTM Fuel Oil #3234423ASTM Fuel Oil #3234423ASTM Fuel Oil #3234411ASTM Fuel Oil #3234423Bable Food1111111Bable Traces							
Arigon Compressed44Ansanit Acid 80%1244Arsenit Acid 80%1244Arsenit Trichinde1111Arsenit Trichinde3444Arsenit Trichinde3444Aphalomic Acid 80%3444Aphalomic Acid 814441Aphalomic Acid 8144441Aphalomic Acid 8144411Aphalomic Acid 81444411Aphalomic Acid 812244411ASTM Fuel Ol #1224442331ASTM Fuel Ol #24444423311 <td>-</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td>	-						
Anomatic hydrocarbons 3 3 3 Assenic At Boby 1 2 4 4 Assenic Trichloride 1 1 1 1 Arsenic Trichloride 3 3 4 4 1 1 Arsenic Trichloride 3 3 4 1 1 1 1 1 1 1 <t< td=""><td></td><td></td><td></td><td></td><td></td><td>4</td><td>4</td></t<>						4	4
Arsenic Tricholde 1 2 4 4 Arsenic Tricholde 1 1 1 1 Arsenic Tricholde 3 4 4 4 Arsenic Tricholde 3 4 4 4 Arsenic Tricholde 1 1 1 1 Arsenic Tricholde 3 4 4 4 Arsenic Tricholde 1 1 1 1 Arsenic Tricholde 1 1 4 4 4 Arsenic Tricholde 2 3 4 4 1 1 Arst Fuel Ol #1 1 1 4 4 2 3 3 Arst Fuel Ol #1 1 <td>÷ .</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td>	÷ .						
Assenic Tricholode 1 1 1 1 Arsenic Tricholde 3 4	-	_				4	4
Asenic Trioxide1							
Aryteurior Acid344Askarel (Transforme Oil)44Astarel (Transforme Oil)44ASTM Fuel Oil #111ASTM Fuel Oil #244ASTM Fuel Oil #2244ASTM Fuel Oil #323ASTM Fuel Oil #3244ASTM Fuel Oil #323ASTM Fuel Di #3444ASTM Fuel Di #3111Barlier Cooper Arsenate1111Barlier Dyrdoxide1111Barlier Dyrdoxide1111Barlier Dyrdoxide1111Barlier Dyrdoxide1111Barlier Dyrdoxide1111Barlier Dyrdoxide2331Berzone Chydraulic Oil2331Berzone Chidebyde4444Berzone Chidebyde444Berzone Chidebyde111Berzone Chidebyde1111Berzone Chidebyde1111Berzone Chidebyde1 </td <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td>							
Akarer Cuill Atphalt444Atphalt114411AtTM Fuel Oil #1114411ATM Fuel Oil #2234411ATM Fuel Oil #3224411ATM Fuel Oil #3224423ATM Fuel Oil #2344423ATM Fuel Oil #3224423ATM Fuel Oil #311111Barly Fool10,10,200,300,50021111Barlum Cubonate111111Barlum Sulfide111111Barlum Sulfide111111Barlum Sulfide111111Barlum Sulfide1111111Barlum Sulfide11111111Barlum Sulfide23			4			4	4
Applait44411ASTM Fuel Oil #1114411ASTM Fuel Oil #2244411ASTM Fuel Oil #2244411ASTM Fuel Oil #32244423ASTM Fuel Oil #2244423ASTM Fuel C444233Baby Food114423Baty Food111111Barlum Chonde111111Barlum Chonde111111Barlum Mydroxide111111Barlum Sufate111111Barlum Sufate111111Barlum Sufate111111Barlum Sufate111111Barlum Sufate1111111Barlum Sufate1111111Barlum Sufate11111111Barlum Sufate111111111111111111111111<	-		4				
ATM Fuel OI #244441ASTM Fuel OI #3234411ASTM Fuel B44423ASTM Fuel C44423Baby Food114423Baby Food114423Baby Food111111Barlum Cytoonate11111Barlum Mytorate11111Barlum Mytorate11111Barlum Mytorate11111Barlum Mytorate11111Barlum Sufface11111Barlum Sufface11111Barlum Sufface11111Barlum Sufface11111Barlum Sufface11111Barlum Sufface23Barlum Sufface23Barlum Sufface23Berlum Charlue23Berlum Sufface23Berlum Sufface23Berlum Charlue23Berlum Charlue </td <td>Asphalt</td> <td>4</td> <td>4</td> <td></td> <td></td> <td></td> <td></td>	Asphalt	4	4				
ASTM Fuel Oil #3234411ASTM Fuel B224411ASTM Fuel B44423ASTM Fuel C44423Baby Food111Barler Types 100, 150, 200, 300, 5002Barlur Cholorate11-11Barlur Cholorate11-11Barlur Sulfate11-23Barlur Sulfate11-11Barlur Sulfate11-11Barlur Sulfate11111Barlur Sulfate1111-Barlur Sulfate1111Barlur Sulfate111Barlur Sulfate111Barlur Sulfate111Barlur Sulfate111Barlur Sulfate23Barlur Sulfate4444Barlur Sulfate111Barlur Sulfate23Benzol Chydraule Coll233<	ASTM Fuel Oil #1	1	1	4	4	1	1
ASTM Fuel A2244411ASTM Fuel B444423ASTM Fuel C444423Baby Food11111Baby Food11111Barlum Carbonate11111Barlum Choirde11111Barlum Mydroxide11111Barlum Sulfate11111Barley141111Barley141111Barley111111Barley1111111Barley1111111Barley11111111Barley111111111Barley23Bernere4444Bernoic Aide23 <td< td=""><td>ASTM Fuel Oil #2</td><td>4</td><td>4</td><td>4</td><td>4</td><td></td><td></td></td<>	ASTM Fuel Oil #2	4	4	4	4		
ASTM Fuel B 4 4 4 4 2 3 ASTM Fuel C 4 4 4 4 2 3 ASTM Fuel C 1	ASTM Fuel Oil #3	2	3	4	4	1	1
ASTM Fuel C 4 4 4 4 2 3 Baby Food 1 1 1 1 1 1 Babit Types 100, 150, 200, 300, 500 22 3 1 1 1 Barium Carbonate 1 1 1 1 1 1 Barium Suffate 1 <td>ASTM Fuel A</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td>	ASTM Fuel A						
Baby Food 1 1 1 Battler Types 100, 150, 200, 300, 500 2 1 1 Barium Carbonate 1 1 1 1 Barium Chloride 1 1 1 1 Barium Chloride 1 1 1 1 1 Barium Sulfide 1 1 1 1 1 1 Barium Sulfide 1 1 1 1 1 1 1 Bariur Sulfide 1 <td>ASTM Fuel B</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td>	ASTM Fuel B						
Bariur Carbonate 1 1 1 Barium Sulfate 1 1 1 1 1 Barium Sulfate 1 1 1 1 1 1 Barium Sulfate 1 1 1 1 1 1 1 Barium Sulfate 1				4	4	2	3
Barium Carbonate 1 1 1 1 Barium Midroxide 1 1 1 1 Barium Sulfide 1 1 1 1 1 Barium Sulfide 1 1 1 1 1 1 Barium Sulfide 1	-		1				
Barium Chloride 1 1 1 1 Barium Hydroxide 1 1 2 3 Barium Sulfide 1 1 1 1 1 Barium Sulfide 1 1 1 1 1 1 Barium Sulfide 1							
Barium Hydroxide 1 1 1 1 1 Barium Sulfide 1 1 1 1 1 Barium Sulfide 1 1 1 1 1 1 Barley 1 4 1 1 1 1 1 Basic Copper Arsenate 1 1 1 1 1 1 1 Beer 1 <t< td=""><td></td><td></td><td></td><td></td><td></td><td></td><td></td></t<>							
Barium Sulfide 1 1 1 1 Barium Sulfide 1 1 1 1 Barley 1 4 1 1 1 Barley 1 1 1 1 1 1 Beer 1 1 1 1 1 1 1 Beer Sugar - Liquor 1							
Barlum Sulfide 1 1 1 1 1 Barlum Sulfide 1 4 4 4 4 Basic Copper Arsenate 1 1 1 1 1 Beer 1 1 1 1 1 1 Beer Stugar - Liquor 1 1 1 1 1 1 Benzoite Stugar - Liquor 1							
Barley 1 4 Basic Cooper Arsenate 1 1 1 Beer 1 1 1 1 Beer Sugar - Liquor 1 1 1 1 Beet Sugar - Liquor 2 - - - Benzatidehyde 4 4 4 - - Benzota 2 3 - - - - Benzota 4 4 4 -		-	-				
Basic Copper Arsenate 1 1 1 1 Beer 1 1 1 1 Beet Sugar - Liquor 1 1 1 1 Beet Sugar - Liquor 2 1 1 1 Benzol So 20 Hydraulic Oil 2 - - - Benzaldehyde 4 4 4 - - - Benzol So 20 Hydraulic Oil 2 3 - <							•
Beer 1 1 1 1 1 Bet Sugar - Liquor 1 1 1 1 1 Bellows 80-20 Hydraulic Oil 2 2 3 4 4 Benzaldehyde 4 4 4 4 4 Benzidhe 4 4 4 4 4 Benzidhe 2 3 4 4 4 Benzidhe 4 4 4 4 4 Benzidhe 4 4 4 4 4 Benzic Aldehyde 4 4 5 3 4 Benzic Aldehyde 1 1 1 1 1 Benzic Aldehyde 1 1 1 1 1 1 Benzic Aldehyde 1 1 1 1 1 1 1<	-		-				
Bellows 80-20 Hydraulic Oil 2 Image: Constraint of the second secon		1	1	1	1		
Benzaldehyde 4 4 4 4 Benzene 4 4 4 4 Benzidine 4 4 4 4 Benzoi Aldehyde 2 3 4 4 Benzoi Aldehyde 4 4 3 4 Benzoi Aldehyde 1 1 5 5 Benzoi Aldehyde 1 1 1 1 Benzoi Aldehyde 1 1 1 1 Benzoi Aldehyde 1 1 1 1 Benzoi Aldehyde 1 1 2 3 4 Benzoi Aldehyde 1 1 2 3 4	Beet Sugar - Liquor	1	1				
Benzene 4 4 4 4 Benzoit Aide 2 3 4 4 Benzoit Aidehyde 4 4 4 4 Benzoit Aidehyde 4 4 3 4 Benzoit Aidehyde 1 3 3 4 Benzoit Aidohoide 1 1 1 1 Benzoit Aidohoide 1 1 1 1 1 Berzies 1 <	Bellows 80-20 Hydraulic Oil	2					
Benzoine 4 4 4 4 Benzoine 4 4 4 4 4 Benzoine 4 4 4 4 4 5 4 4 5 4 4 5 4 4 5	Benzaldehyde	4	4				
Benzoic Acid 2 3 4 4 Benzoic Aldehyde 4 4 3 4 Benzol 4 4 3 4 Benzol Aldehyde 4 4 3 4 Benzol Kicker 4 4 3 4 Benzol Kicker 4 4 3 4 Benzol Kicker 1 3 3 4 Benzol Kicker 1 3 3 4 Benzol Kicker 4 4 5 3 4 Benzol Chloride 4 4 5 5 5 5 Benzyl Chloride 1	Benzene	4	4	4	4		
Benzoic Aldehyde4434Benzol44334Benzyl Alcohol13344Benzyl Alcohol444444Berries1111111Bismuth Carbonate1111111Black Liquor1111111Black Liquor234434Bleach 12.5% Active CL234434Borica CAxide111234Boric CAxide111111Brake Fluid (Petroleum Base)22111Brake Fluid (Synthetic Base)211	Benzidine						
Benzol44334Benzotrichloride441111Benzyl Alcohol111111Benzyl Chloride4411111Bismuth Carbonate1111111Black Liquor11111111Black Liquor23344111			_			4	4
Benzotrichloride 4 4 3 3 Benzyl Alcohol 1 1 3 3 Benzyl Chloride 4 4 4 4 Berries 1 1 1 1 Bismuth Carbonate 1 1 1 1 Black Liquor 1 1 1 1 Black Liquor 2 3 3 4 Bleach 12.5% Active CL 2 3 3 4 Borax 1 2 3 3 4 Bordeaux Mixture 1 1 2 3 1 2 Boric Acid 1 1 1 4	-						
Benzyl Alcohol133Benzyl Chloride444						3	4
Benzyl Chloride 4 4 Berries 1 1 Bismuth Carbonate 1 1 Bismuth Carbonate 1 1 Black Liquor 2 3 Black Liquor 2 3 Black Liquor 1 2 Black Liquor 1 1 Black Liquor 1 1 Black Liquor 1 1 Borax 1 1 Borax 1 1 Boric Acid 1 1 Boric Oxide 1 1 Brake Fluid (Petroleum Base) 2 1 Brake Fluid (Synthetic Base) 2 1			4	2	2		
Berries111Bismuth Carbonate1111Black Liquor11111Blast Furnace Gas44Bleach 12.5% Active CL2334-Borax121212Bordeaux Mixture11Boric Acid111Boric Oxide1111-Borax Fluid (Petroleum Base)22Brake Fluid (Synthetic Base)2	-		4	3	3		
Bismuth Carbonate111Black Liquor111Blast Furnace Gas44-Bleach 12.5% Active CL233Borax1212Bordeaux Mixture11-Boric Acid114Boric Oxide11-Boron Triflouride111Brake Fluid (Petroleum Base)2Brake Fluid (Synthetic Base)2							
Black Liquor111Blast Furnace Gas441Bleach 12.5% Active CL233Borax1212Bordeaux Mixture111Boric Acid114Boric Oxide111Boron Triflouride111Brake Fluid (Petroleum Base)221Brake Fluid (Synthetic Base)211						1	1
Blast Furnace Gas444Bleach 12.5% Active CL2334Borax121212Bordeaux Mixture11444Boric Acid11444Boric Oxide11111Boron Triflouride11111Brake Fluid (Petroleum Base)22111						· ·	·
Bleach 12.5% Active CL234Borax1212Bordeaux Mixture1144Boric Acid1144Boric Oxide1111Boron Triflouride1111Brake Fluid (Petroleum Base)2211			-				
Borax1212Bordeaux Mixture1144Boric Acid1144Boric Oxide1111Boron Triflouride1111Brake Fluid (Petroleum Base)2211Brake Fluid (Synthetic Base)2111						3	4
Bordeaux Mixture1144Boric Acid1144Boric Oxide1111Boron Triflouride1111Brake Fluid (Petroleum Base)2211Brake Fluid (Synthetic Base)2111							
Boric Oxide11Boron Triflouride111Brake Fluid (Petroleum Base)211Brake Fluid (Synthetic Base)211	Bordeaux Mixture	1					
Boron Triflouride111Brake Fluid (Petroleum Base)221Brake Fluid (Synthetic Base)211	Boric Acid	1	1			4	4
Brake Fluid (Petroleum Base)2Brake Fluid (Synthetic Base)2	Boric Oxide	1					
Brake Fluid (Synthetic Base) 2	Boron Triflouride	1	1			1	1
Brine 1 1 1 1 2 3							
	Brine	1	1	1	1	2	3

CHEMICAL RESISTANCE TABLES PVC, EPDM & POLYURETHANE



1-EXCELLENT	2-GOOD	3-LIN	1ITED	4-UI	NSATISFAC ⁻	TORY		
HOSE CONSTRUCTION WITH TEMPERATURE								
MATERIAL	PV0 68			1 (F°) 104	POLYURETHANE (F°) 68 104			
Bromic Acid	1	2			4	4		
Bromine - Liquid	4	4			4	4		
Bromine - Water	4	4			4	4		
Bromobenzene	4	4				1		
Bromochloromethane	4	4						
Bromotoluene	4	4						
Bunker Oil	4	4	4	4				
Butadiene	3	4	-					
Butane	1	1			1	1		
Butanol - Primary	4	4			3	4		
Butanol - Secondary	4	4			3	4		
Butter	2	3						
Butyl Acetate	1							
Butyl Alcohol	1	2			3	4		
Butyl Cellosolve	4	4						
Butyl Mercaptan	4	4						
Butyl Phenol	3	4						
Butyl Stearate	1							
Butylene	1	2			1	1		
Butyric Acid 20%	3	4			3	4		
Butynedial	4	4			4	4		
Cake Alum Solution	1							
Calcium Arsenate	1							
Calcium Bisulfate	1	1						
Calcium Bisulfide	2							
Calcium Bisulfite	1	1			1	1		
Calcium Carbonate	1	1			1	1		
Calcium Chlorate	1	1			2	3		
Calcium Chloride	1	1	1	1	3	4		
Calcium Hydrosulfide	2					-		
Calcium Hydroxide	1	1	1	1	2	3		
Calcium Hypochlorite	1	1			4	4		
Calcium Metasilicate	1							
Calcium Nitrate	1	1			1	1		
Calcium Silicate Calcium Sulfate	1							
Calcium Sulfide	2	1			1	1		
Cane Sugar Liquors	2							
Carbolic Acids	4	4						
Carbon Bisulfide	1	1						
Carbon Dioxide	1	1						
Carbon Disulfide	4	4	4	4				
Carbon Dioxide	1	1			1	1		
Carbon Disulfide	4	4				-		
Carbon Monoxide	1	1			1	1		
Carbon Tetrachloride	4	4	4	4	3	4		
Carbolic Acid	4	4			_			
Carbonic Acid	1	1	2	2	4	4		
Carrots	1	1						
Casein	1	2			1	1		
Castor Oil	1	1			1	1		
Catsup	1	2						
Caustic Potash	1	1			3	4		
Caustic Soda	1	1			3	4		
Cellosolve	3	4			2	3		
Collulara Acatata					1			

1

1

1

2

Cellulose Acetate Cellulose Butyl

Cheese



1-EXCELLENT

2-GOOD

3-LIMITED

HOSE CONSTRUCTION WITH TEMPERATURE

4-UNSATISFACTORY

MATERIAL	PVC (F°) 68 104	EPDM (F°) 68 104	POLYURETHANE (F°) 68 104
Cherries	1 1		
China-Wood Oil	2		
Chlordane	2		
Chloracetic Acid	1 4		4 4
Chloral Hydrate	1 1		2 3
Chloric Acid 20%	1 1		4 4
Chlorinated Hydrocarbons	1 1		4 4
Chlorinated Solvents	4 4		
Chlorine Gas - Dry	1 1	4 4	4 4
Chlorine Gas - Moist	3 4	4 4	4 4
Chlorine Triflouride	4 4		
Chloroacetyl Chloride	1		
Chlorobenzene	4 4		
Chlorobromomethane	4 4		
Chloromethane Chloroform	4 4 4 4		
Chloropentane	4 4 4 4		
Chloropicrin Mixture	4 4		
Chlorotoluene	4 4 4		
Chlorox	1		
Chlorsulfonic Acid	3 4		4 4
Chocolate	2 3		
Chocolate Syrup	1		
Chromic Chloride	1		
Chrome Alum	1 1		1 1
Chromic Acid 25%	2 3	4 4	4 4
Chromic Acid 50%	2 3		4 4
Chromium Trioxide	4 4		
Cider	2		2 3
Citgo FR Fuels	2		
Coal Gas	1		
Coal Tar	4 4		4 4
Coconut Oil	3 4		1 1
Cola Beverage	1 1		
Copper Chloride	1 2		1 1
Copper Cyanide	1 1		
Copper Flouride 2%	1 1		
Copper Nitrate	1 2		1 1
Copper Sulphate	1 2		1 1
Core Oils	1 1		
Corn Oils	1 2		
Cottonseed Oil Creosote	2 3 4 4		1 1
Cresylic Acid 50%	4 4 4		4 4
Crude Oil Sour	1 1		1 1
Crude Oil Sweet	1 1		1 1
Crude Wax			
Cupric Chloride	1		
Cupric Cyanide	1		
Cupric Nitrate	1		
Cupric Sulfate	1		
Cyanide, Copper	1		
Cyanide, Silver	1		
Cyanide, Sodium	1		
Cyclohexane	4 4		
Cyclohexanol	4 4		3 4
Cyclohexanone	4 4		4 4
Cymene	4 4		
	I		



1-EXCELLENT	2-GOOD	3-LIN	ITED	4-UN	SATISFAC	ORY		
HOSE CONSTRUCTION WITH TEMPERATURE								
MATERIAL	PV0 68	C (F°) 104	EPDN 68	1 (F°) 104	POLYURE1 68	THANE (F°) 104		
Decanol	4	4						
Deicing Fluid	1	1						
Demineralized Water	1	1			2	4		
Denatured Alcohol	1							
Detergents, Synthetic	1	2						
Developers, Photographic	1	1						
Dextrin	1							
Dextron	2							
Dextrose	1	2			1	1		
Diacetone	4	4			3	4		
Diacetone Alcohol	4	4			3	4		
Diammonium Phosphate	1							
Diazinon Diazo Salts	2	1						
Dibutyl Phthalate	1							
Dibutylamine	4	4						
Dichlorobenzene	4	4						
Dichlorobenzyl Chloride	4	4						
Dichloroethane	4	4						
Dichloroethylene	4	4						
Dichloromethane	4	4						
Diesel Oils	3	4						
Diethanolamine	2							
Diethyl Ether	2							
Diethyl Ketone	4	4						
Diethyl Oxalate	4	4						
Diethylene Dioxide	2							
Diethylene Ether	4	4		1				
Diethylene Glycol	1	2	1	1				
Diglycolic Acid Dihydroxethyl Ether	1	Z						
Dimethylamine	4	4			4	4		
Dimethybenzene	4	4						
Dimethylcarbonal	2	•						
Dimethylketone	4	4						
Dioctyl Phthalate	4	4						
Dioctyl Phosphite	4	4						
Dioxane	4	4						
Disodium Phosphate	1	1			1	1		
Distilled Water	1	1			2	4		
DMB (Dimethylbenzene)	4	4						
Duro Oils	2	_						
EDB (Ethylene Dibromide)	4	4						
Eggs	1	1						
Emulsions, Photographic Enamels	1	1						
Essential Oils	2							
Ethanolamine	2							
Ethers	4	4			2	3		
Ethyl Acetate	4	4			2	-		
Ethyl Acrylate	4	4						
Ethyl Bromide	4	4						
Ethyl Chloride	4	4			4	4		
Ethyl Ether	4	4			2	3		
Ethyl Ether Acetate	1							
Ethyl Mercaptan	4	4						
Ethyl Methyl Ketone	4	4						
Ethylbutanol	1							



HOSE CONSTRUCTION WITH TEMPERATURE

1-EXCELLENT

2-GOOD

3-LIMITED

MATERIAL	PVC (F°)	EPDM (F°)	POLYURETHANE (F°)			
	68 104	68 104	68 104			
Ethylbutyl Alcohol	1					
Ethylene Bromide	1 4		4 4			
Ethylene Chlorohydrin	4 4					
Ethylene Dibromide	4 4					
Ethylene Dichloride	4 4		4 4			
Ethylene Glycol	1 1		2 3			
Ethylene Oxide	4 4		4 4			
Ethylhexanol	1					
Ethylhexyl Acrylate	4 4					
Ethylhexyl Alcohol	1					
Fatty Acid Fatty Alcohol, Blend	2					
Ferric Chloride	1 1		2 3			
Ferric Nitrate	1 1		2 5			
Ferric Sulphate	1 1		1 1			
Ferrous Chloride	1 1		1 1			
Ferrous Nitrate	2					
Ferrous Sulfate Solution	1					
Fertilizer	2					
Figs	1 1					
Fish Solubles	1 1					
Fixing Solutions, Photographic	1 2					
Flour	1 4					
Flourobic Acid	1 1					
Flourine	4 4		4 4			
Fluosilic Acid	4 4					
Foric Acid	1 3		4 4			
Formaldehyde Solution (to 50%)	1	3 3				
Formalin	1	2 2				
Formic Acid 3%	1 2 1 2	2 2 2 2				
Formic Acid 10% Formic Acid 25%	1 2 1 2	3 3	4 4 4 4			
Formic Acid 25%	3 4	3 3	4 4			
Freon-12	1 2	5 5	1 1			
Fructose	1 1		1 1			
Fruit Pulps and Juices	1 1		1 1			
Fuel Oil	2 3		1 1			
Furnaric Acid	4 4					
Furan	4 4					
Furfural	4 4		4 4			
Furfuryl Alcohol	1 3					
Fusel Oil	1					
Gallic Acid Solution	4 4					
Gasohol	4 4					
Gas - Cook Oven	2 2		2 2			
Gas - Natural (Dry)	1 1		1 1			
Gas - Natural (Wet)	1 1		1 1			
Gasoline Gasoline Refined	4 4					
Gasoline - Refined	3 4 4 4	4 4 4 4				
Gasoline - Unleaded Gasoline - White	4 4 4 4	4 4 4 4				
Gelatin	4 4	7 7	1 1			
Gin	1 2		· · · · ·			
Ginger Ale	1 1					
Glacial Acetic Acid	4 4					
Glucose	1 1		1 1			
Glue	1					
Glycerol	1 1					
*						



HOSE CONSTRUCTION WITH TEMPERATURE MATERIAL PVC (F°) 68 EPDM (F°) 68 POLYURETHANE (F°) 68 Glycol 1	EXCELLENT	2-GOOD	3-LII	MITED	4-UN	SATISFAC	FORY	
Glycol 1 1 68 104 68 104 Glycol 1	HOS	E CONSTRU		ИТН ТЕМ	PERATUR	{E		
Glycolic Acid 30% 1 1 1 Grape Juice 1 1 1 Grape fuit Juice 1 1 1 Grease 1 1 1 Green Liquor (Paper) 1 1 1 Heptachlor 4 4 1 Heptane 3 4 1 Heptanol 1 1 1 Hexane 3 4 3 4 Honey 1 1 1 1 HYdraulic Fluid 1 1 1 1 Hydraulic Fluid HF-18, HF-20 2 1 1 1 Hydrobromic Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 48% 3 3 3 4 4	ERIAL							
Glycolic Acid 30% 1 1 1 Grape Juice 1 1 1 Grape fuit Juice 1 1 1 Grease 1 1 1 Green Liquor (Paper) 1 1 1 Heptachlor 4 4 1 Heptane 3 4 1 Heptanol 1 1 1 Hexane 3 4 3 4 Honey 1 1 1 1 HYdraulic Fluid 1 1 1 1 Hydraulic Fluid HF-18, HF-20 2 1 1 1 Hydrobromic Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 48% 3 3 3 4 4			1			1	1	
Grape Juice 1 1 1 Grapefruit Juice 1 1 1 Grease 1 1 1 Grease 1 1 1 Grease 1 1 1 Grease Liquor (Paper) 1 1 1 Heptanlo 4 4 1 Heptanol 1 1 1 Heptanol 1 1 1 Heptanol 1 3 4 Honey 1 1 3 4 HYdraulic Fluid 1 1 3 4 Hydraulic Fluid 1 2 2 4 Hydrobromic Acid 4 3 3 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 48% 3 3 4 4 Hydrochloric Acid 48% 3 3 2 4 4 Hydr	Acid 30%							
GrapeFult Juice 1 1 Grease 1 1 Green Liquor (Paper) 1 1 Heptachlor 4 4 Heptane 3 4 Heptanol 1 1 Heptanol 1 1 Hexane 3 4 3 4 Honey 1 1 4 3 4 Honey 1 1 4 4 3 4 Hydroliur Fluid 1 4						-	-	
Grease 1 1 Green Liquor (Paper) 1 1 Heptachlor 4 4 Heptane 3 4 Heptanol 1 1 Heptanol 1 1 Hexane 3 4 Honey 1 1 HYdroulic Fluid 1 1 Hydraulic Fluid HF-18, HF-20 2 4 Hydro-Drive Oil (Houghton) 2 1 Hydrochloric Acid 10% 1 1 2 Hydrochloric Acid 48% 3 3 4 Hydroflouric Acid 4% 2 3 3 Hydroflouric Acid 10% 3 3 4 Hydroflouric Acid 4% 3 3								
Heptane 4 4 Heptane 3 4 Heptane 3 4 Heptanol 1 1 Hexane 3 4 3 4 Honey 1 1 3 4 Hydraulic Fluid 1 4 4 3 3 Hydraulic Fluid HF-18, HF-20 2 4 4 3 3 4 Hydro-Drive Oil (Houghton) 2 4 4 3 3 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 3 4 3 3 4 4 Hydrofhouric Acid 48% 3 3 2 2 2 4 4 Hydrofhouric Acid 48% 3 4 3 3 3 4 4 Hydrofhouric Acid 48% </td <td></td> <td>1</td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td>		1						
Heptane 3 4 1 Heptanol 1 1 1 Hexane 3 4 3 4 Honey 1 1 3 4 Honey 1 1 1 1 1 HPO (Sodium Thiosulfate) 1 1 1 1 1 1 Hydraulic Fluid 1<	juor (Paper)	1	1					
Heptanol 1 J<	or	4	4					
Hexane 3 4 Honey 1 1 1 HPO (Sodium Thiosulfate) 1 1 1 Hydraulic Fluid 1 1 1 Hydraulic Fluid HF-18, HF-20 2 4 4 Hydro-Drive Oll (Houghton) 2 - - - Hydrochloric Acid 10% 1 1 2 4 4 Hydrochloric Acid 48% 3 4 3 3 4 4 Hydrofflouric Acid 48% 3 4 3 3 4 4 Hydrofflouric Acid 48% 3 4 3 3 4 4 Hydrofflouric Acid 48% 3 4 3 3 4 4 Hydrofflouric Acid 48% 3 4 3 3 4 4 Hydrofflouric Acid 48% 3 4 3 3 4 4 Hydrofflouric Acid 60% 3 4 3 3 4 4		3	4			1		
Honey 1 1 1 HPO (Sodium Thiosulfate) 1 1 1 Hydraulic Fluid 1 1 1 Hydraulic Fluid HF-18, HF-20 2 1 1 Hydrazine 4 4 3 3 Hydrobromic Acid 4 4 3 3 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 48% 3 4 3 3 4 4 Hydroflouric Acid 4% 2 3 2 2 4 4 Hydroflouric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 4% 2 3 2 2 4 4 Hydroflouric Acid 4% 3 3 2 2 4 4 Hydroflouric Acid 10% 3 3 3 4 4 Hydroflouric Acid 48% 3 4 3 3 4 4 Hydroflouric Acid 48% 3 4 3 3 4 4<								
HPO (Sodium Thiosulfate)1Hydraulic Fluid1Hydraulic Fluid HF-18, HF-202Hydrazine44Hydro-Drive Oil (Houghton)2Hydrobromic Acid44Hydrochloric Acid 10%11Hydrochloric Acid 48%34Hydroflouric Acid 48%33Hydroflouric Acid 10%11Hydroflouric Acid 48%3Hydroflouric Acid 10%3Hydroflouric Acid 48%3Hydroflouric Acid 10%3Hydroflouric Acid 10%3Hydroflouric Acid 60%3Hydroflouric Acid 60%4Hydroflousilicic Acid4Hydroflousilicic A						3	4	
Hydraulic Fluid 1 1 Hydraulic Fluid HF-18, HF-20 2 Hydrazine 4 4 Hydro-Drive Oil (Houghton) 2			1					
Hydraulic Fluid HF-18, HF-20 2 Hydrazine 4 4 Hydro-Drive Oil (Houghton) 2	· · · · · · · · · · · · · · · · · · ·	-						
Hydrazine 4 4 Hydro-Drive Oil (Houghton) 2		-						
Hydro-Drive Oil (Houghton) 2 Hydrobromic Acid 4 4 3 3 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 48% 3 4 3 3 4 4 Hydrochloric Acid 48% 2 3 2 2 4 4 Hydroflouric Acid 4% 2 3 3 2 2 4 4 Hydroflouric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 48% 3 4 3 3 4 4 Hydroflouric Acid 60% 3 4 3 3 4 4 Hydroflouric Acid 60% 3 4 4 4 4								
Hydrobromic Acid 4 4 3 3 Hydrochloric Acid 10% 1 1 2 2 4 4 Hydrochloric Acid 10% 3 4 3 3 4 4 Hydrochloric Acid 48% 3 4 4 3 3 4 4 Hydroflouric Acid 4% 2 3 2 2 4 4 Hydroflouric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 48% 3 4 3 3 4 4 Hydroflouric Acid 60% 3 4 4 4 4 Hydrofluosilicic Acid 4 4 4 4 4			4					
Hydrochloric Acid 10%112244Hydrochloric Acid 48%343344Hydrochloric Acid 48%44Hydroflouric Acid 4%232244Hydroflouric Acid 10%332244Hydroflouric Acid 48%343344Hydroflouric Acid 60%34444Hydrofluosilicic Acid44444			4	3	3			
Ydrochloric Acid 48%343344Hydrocyanic Acid44Hydroflouric Acid 4%232244Hydroflouric Acid 10%332244Hydroflouric Acid 48%343344Hydroflouric Acid 60%34444Hydroflousilicic Acid44444						4	4	
Hydrocyanic Acid444Hydroflouric Acid 4%232244Hydroflouric Acid 10%332244Hydroflouric Acid 48%343344Hydroflouric Acid 60%34444Hydroflousilicic Acid44444								
Hydroflouric Acid 4% 2 3 2 2 4 4 Hydroflouric Acid 10% 3 3 2 2 4 4 Hydroflouric Acid 48% 3 4 3 3 2 2 4 4 Hydroflouric Acid 48% 3 4 3 3 4 4 Hydroflouric Acid 60% 3 4 4 4 4 Hydrofluosilicic Acid 4 4 4 4			-	5	2	-	•	
Hydroflouric Acid 10%332244Hydroflouric Acid 48%343344Hydroflouric Acid 60%34444Hydrofluosilicic Acid4444		2	3	2	2	4	4	
Hydroflouric Acid 60%344Hydrofluosilicic Acid444		3	3	2	2	4	4	
Hydrofluosilicic Acid 4 4 4	uric Acid 48%	3	4	3	3	4	4	
	uric Acid 60%	3	4			4	4	
Hydrogen 1 2 1 1	osilicic Acid	4	4			4	4	
		1	2			1		
Hydrogen Bromide (Dry) (Liquid) 1 1								
Hydrogen Cyanide 1 1 4 4	-					4	4	
Hydrogen Peroxide 4 4								
Hydrogen Peroxide 12% 1 2 2 2 Hydrogen Peroxide 50% 1 3 3 2 3						2	2	
j. j. j				3	3			
Hydrogen Peroxide 90%444Hydrogen Phosphide13						7	4	
Hydrogen Sulfide - Aqueous Solution 1 1								
Hydrogen Sulfide - Dry 1 1 1	-		-					
Hydrolube (Water Glycol) 1 1		1	1					
Hydrolubric Oil 2		2						
Hydroquinone Solution 2								
Hydroxylamine Sulfate 1 1	amine Sulfate	1	1					
Hydrochlorous Acid 1 1 3 4	orous Acid	1	1			3	4	
lodine 4 4		4	4					
Iron Acetate Liquor 1	ate Liquor	1						
Iron Salts 1								
Iron Sulfate Solution 1								
Isobutanol 2								
Isobutyl Alcohol 2 Isooctane 4 4 4					4			
			4	4	4			
Isopropanol 2 Isopropyl Acetate 4 4			4					
Isopropyl Alcohol 1 2 3 3				2	3			
Isopropyl Ether 4 4					-			
JP 3, 4, 5 4 4 2 3				2	3			
Jelly 1 1				_	-			
Jet Fuel - All Types 4 4	All Types							
Karo Syrup 1 1			1					
Kerosene 4 4 4 1 2		4	4	4	4	1	2	
Ketones 4 4		4	4					
Kraft Liquor (Paper) 1 1	ior (Paper)	1	1					



1-EXCELLENT

2-GOOD

3-LIMITED

HOSE CONSTRUCTION WITH TEMPERATURE

MATERIAL	DVC	PVC (F°)		EPDM (F°)		POLYURETHANE (F°)		
	68	104	68			68	104	
LacquerThinner	3	4				2		
Lactic Acid 28%	1	1				4	4	
Lard	2	3						
Lard Oil	1	2				1	2	
Latex Paint	1							
Lauric Acid	1	1				3	4	
Laurel Chlorite	1	1				1	2	
Lauryly Sulfate	1	1						
Lead Acetate	1	1				1	1	
Lead Nitrate Solution	1							
Lead, Tetraethyl	1							
Lemon Juice	1	2						
Ligroin	4	4						
Lime, Chlorinated	2							
Lime, Sulfur	1	1						
Linoleic Acid	1	_						
Linseed Oil	1	1				1	1	
Liquid Soap	2	2						
Liquors	1 4	2 4					1	
Lubricating Oils Machine Oil - Under 135°F	4 2	4				1	1	
Magnesium Carbonate	2	1				1	1	
Magnesium Hydroxide	1	1	2	2		2	3	
Magnesium Nitrate	1	1	-	2		1	1	
Magnesium Sulfate Solution	1							
Malathion	1							
Maleic Acid Solution	4	4						
Manganese Salts	1							
Manganese Sulfate Solution	1							
Mayonnaise	1	1						
MBK (Methyl Butyl Ketone)	4	4						
MEA (Ethanolamine)	2							
MEK (Ethyl Methyl Ketone)	4	4	3	3		4	4	
Mercuric Chloride	2	2				2	3	
Mercuric Chloride Solution	2							
Mercuric Cyanide	2	2						
Mercuric Nitrate	2	2		_		2	2	
Mercury	2	2	2	2				
Mesitylene	4	4						
Mesityl Oxide	4	4						
Mesitylene Methanol	4	4				4	4	
Methanol Methyl Acetate	4	4 4				4	4	
Methyl Acetone	4	7						
Methyl Alcohol	3	4				4	4	
Methyl Bromide	4	4					-	
Methyl Butanathiol	4	4						
Methyl Butanol	1	-						
Methyl Chloride	4	4				4	4	
Methyl Chloroform	4	4					-	
Methyl Cyanise	1							
Methyl Ethyl Ketone	4	4						
Methyl Isobutenyl Ketone	4	4						
Methyl Isobutyl Ketone	4	4						
Methyl Isopropyl Ketone	4	4						
Methyl Methacrylate	1							
Methyl Methacrylate Monomer	4	4						
Methyl Propyl Ketone	4	4						
			1					



1-EXCELLENT 2	-GOOD	3-LIN	IITED	4-UN	SATISFACT	ORY
HOSE	CONSTRU			PERATUR	E	
MATERIAL	PVC 68	: (F°) 104	EPDN 68	1 (F°) 104	POLYURET 68	HANE (F°) 104
Methyl Slaicylate	1					
Methyl Sulfate	1					
Methylamine	4	4				
Methylaniline	4	4				
Methylene Bromide	4	4				
Methylene Chloride	4	4 4				
Methylene Dichloride Milk	4	4			1	1
Mineral Oils	1	2			1	1
Molasses	1	1			1	1
Monochlorobenzene	4	4				
Monomethylamine	4	4				
Monosodium Phosphate	1					
Motor Oil	3					
Muriatic Acid	4	4				
n-Octane Nexthering Asid	4	4				
Napthenic Acid Nickel Chloride Solution	1	1			1	1
Nickel Nitrate Solution	2				1	1
Nickel Plating Solution	4	4			•	•
Nickel Salts	2					
Nickel Sulfate Solution	1					
Nicotine	1	1			1	1
Nicotine Acids	1	2			3	4
Nicotine Salts	1					
Niter Cake	1	2		2		
Nitric Acid 10% Nitric Acid 40%	1	2 3	2	2 2	4 4	4 4
Nitric Acid 40%	3	4	3	2 3	4	4
Nitric Acid 68%	3	4	4	4	4	4
Nitric Acid 70%	4	4	4	4	4	4
Nitrobenzene	4	4	3	3	4	4
Nitrogen	1					
Nitrogen Oxide	4	4				
Nitromethane	4	4				
Nitrous Acid (Up to 10%)	1					
Nitrous Oxide Octadecanoic Acid	1	1			1	1
Octanol	2					
Octyl Alcohol	2					
Oil of Turpentine	1					
Oils, Animal	2					
Oils, Mineral	4	4				
Oils, Petroleum	1	2			1	1
Oleic Acid	2	3			4	4
Oleum Olive Oil	4 2	4 2			4	4
Ortho-Dichlorobenzene	4	4				
Ortho-Xylene	4	4				
Oxalic Acid	4	4	3	3		
Oxygen	1	1	2	2	1	1
Ozone	3	4	2	2		
Paint	1					
Palmitic Acid 10%	1	2			4	4
Palmitic Acid 70%	3	4			4	4
Paraformaldehyde	1	1				
Peaches Peanut Butter	1	1 2				
r canat batter	· · · · ·	-				



1-EXCELLENT

2-GOOD

3-LIMITED

HOSE CONSTRUCTION WITH TEMPERATURE

MATERIAL	PVC (F°)	EPDM (F°)	POLYURETHANE (F°)
	68 104	68 104	68 104
Peanut Oil	2		
Peas	1 1		
Pentachlorophenol in Oil	4 4		
Pentane	3 4		
Pentanone	4 4		
Pentasol	2		
Perchloric Acid	4 4	2 2	
Perchloroethylene	4 4		
Petrol	4 4		
Petroleum Ether	3 3		
Petroleum Naptha	4 4		
Petroleum Oils (Refined)	1		
Petroleum Oils (Sour)	2		
Phenol	4 4		
Phenol Acid	4 4		
Phenyl Chloride	4 4		
Phenolhydrazine	4 4		
Phenolhydrazine Hydrochloride	3 4		
Phosgene (Gas)	1 2		
Phosgene (Liquid)	4 4		
Photographic Fixing Solutions	1		
Phosphorous (Yellow)	2 3		
Phosphorous Pentoxide	4 4		
Phosphorous Trichloride	1 1		1 1
Photographic Chemicals	1 1		1 2
Picric Acid	4 4		4 4
Pinene	4 4		
Pitch	2 3		
Plating Solutions	1 2		1 1
Polyethylene Glycol	2		
Potash Potassium Acetate	1		
Potassium Acid Sulfate	1 1		1 1
Potassium Antimonate	1 1		1 1
Potassium Bicarbonate	1 1		1 1
Potassium Bichromate	1 1		1 1
Potassium Bisulfite	1 1		
Potassium Borate 1%	1 1		1 1
Potassium Bisulfate	1		
Potassium Bromate 10%	1 1		1 1
Potassium Bromide	1 1		1 1
Potassium Carbonate	1		
Potassium Chlorate	1		
Potassium Chloride	1 1		1 2
Potassium Chromate	1		2 2
Potassium Cuprocyanide	1		
Potassium Cyanide	1 1		1 1
Potassium Dichromate	1 1	2 2	2 2
Potassium Ferrocyanide	1 1		1 1
Potassium Hydrate	2		
Potassium Hydroxide	1 1	2 2	
Potassium Hypochlorite	2 3		4 4
Potassium Iodine	1		
Potassium Nitrate	1 1		1 1
Potassium Perborate	1 1		1 1
Potassium Perchlorite	1 1		2 3
Potassium Permanganate	4 4	3 3	
Potassium Persulfate	1		



1-EXCELLENT	2-GOOD	3-LI	MITED	4-UN	NSATISFACT	ORY
	HOSE CONSTRU			IPERATU	RE	
MATERIAL	PVC 68	(F°) 104	EPD 68	M (F°) 104	POLYURET 68	HANE (F°) 104
Potassium Sulfate	1					
Potassium Sulfide	1	1			1	1
Potassium Sulfite	2					
Potassium Thiosulfate Potatoes	1	1				
Propane	1	1			1	1
Propargyl Alcohol	1	1			1	1
Propyl Alcohol	1	2	2	2	2	3
Propylene Dichloride	4	4			4	4
Propylene Glycol	1				4	4
Prune Juice	1	1				
Puropale RX Oils	2 4	4				
Pyrene Pyrethrum	2	4				
Pyridine	4	4				
Pyrogard C, D	2	-				
Red Oil	2					
Regal Oils R&O	2					
Rubilene Oils	2					
Salicylic Acid	1					
Salt Water	1	1	2	2	2	4
Sauerkraut Selenic Acid	2	2			4	4
Sewage	2	2			Ť	7
Shortening	2	3				
Silicic Acid	1	1			4	4
Silicone Greases	2		2	2		
Silicone Oils	2		2	2		
Silver Cyanide	1	1			1	1
Silver Plating Solution	1	2			1	1
Skydrol 500A & 7000 Soap	4	4 1	2	2	2	4
Soda Ash	1		2	2	2	-
Soda Water	1	1				
Sodium Acetate	1	1			1	1
Sodium Aluminate	2					
Sodium Arsenite	1	1			1	1
Sodium Benzoate	1	2			1	1
Sodium Bicarbonate	1	1			1	1
Sodium Bichromate Solution Sodium Bisulfite	2					
Sodium Borate	1					
Sodium Bromide	1	1			1	2
Sodium Carbonate (Soda Ash)	1	1			1	1
Sodium Chlorate	2	3			2	2
Sodium Chloride	1	1			1	2
Sodium Chlorite Solution	2					
Sodium Chromate	2	_				-
Sodium Cyanide	1	1 2			1	1 2
Sodium Dichromate Sodium Ferricyanide	1	2			1	2
Sodium Fluoride (70%)	1	2			1	2
Sodium Hydrate	2					
Sodium Hydrochlorite	2					
Sodium Hydrosulfide	1					
Sodium Hydrosulfite	2					
Sodium Hydroxide 10%	1	1	3	3	3	4
Sodium Hydroxide 35%	1	2			4	4



1-EXCELLENT

2-GOOD

3-LIMITED

HOSE CONSTRUCTION WITH TEMPERATURE

HOSE CONSTRUCTION WITH TEMPERATORE							
MATERIAL	PVC 68	(F°) 104	EPDI 68	M (F°) 104	POLYURET 68	HANE (F°) 104	
Sodium Hydroxide 50%	1	3					
Sodium Hypochlorite (20%)	1	1	3	3	4	4	
Sodium Hyposulfate	1						
Sodium Metaphosphate	1						
Sodium Nitrate	1	1			1	1	
Sodium Nitrite	1	1	_	_	1	1	
Sodium Peroxide	1		2	2			
Sodium Phosphate	1	2	2	2			
Sodium Phosphate Acid Sodium Silicate	2 1	2					
Sodium Sulfate	1						
Sodium Sulfhydrate	2						
Sodium Sulfide	1	1			1	1	
Sodium Sulfite	1	1			1	1	
Sodium Sulphrydate	2						
Sodium Thiosulfat	1	1			1	2	
Soinus Oils	1						
Sour Crude Oil	4	4					
Soya Beans	1	4					
Soybean Oil	1	1	4	4			
Spent Acid	4	4					
Spinach	1	1					
Squash	1	1					
Stannic Chloride	2						
Stannis Chloride	1	1			1	2	
Starch	1						
Starch Gum	1						
Stearic Acid	1						
Stoddard Solvent	2						
Straight Synthetic Oils	2						
Styrene	4	4					
Sugar - All Forms	1	1					
Sulfamic Acid	4	4					
Sulfate Liquors Under 150°F	1 2	2					
Sulfur Sulfur Chloride	2	Z					
	2		2	2			
Sulfur Dioxide (Dry) Sulfur Dioxide (Liquid)	4	4	2 2	2			
Sulfur Hexafluoride (Gas)	2		2	2			
Sulfur Trioxide	1						
Sulfuric Acid 10%	1	2	3	3	3	4	
Sulfuric Acid 70%	1	2	4	4	4	4	
Sulfuric Acid 95%	3	3	4	4	4	4	
Sulfurous Acid	2	3	3	3	4	4	
Sulfur Dioxide Gas - Dry	1	1					
Sulfur Dioxide Gas - Wet	4	4					
Sulfur Dioxide - Liquid	3	4					
Sun R&O Oils	2						
Suntac HP Oils	2						
Suntac WR Oils	2						
Sunvis Oils 700, 800, 900	2						
Synthetic Oil (Citgo)	2						
Tall Oil	4	4					
Tallow	2						
Tannic Acid	1	1	3	3	3	4	
Tanning Liquors	1	1			2	3	
Tar Oil	2	_					
Tartaric Acid	1	2			3	4	



1-EXCELLENT 2	-GOOD	3-LI	MITED	4-UN	ISATISFAC	TORY
HOSE	CONSTRU			IPERATU	RE	
MATERIAL	PV0 68	C (F°) 104	EPD 68	DM (F°) 104	POLYURE 68	THANE (F°) 104
TEA (Triethanolamine)	2	3				
Tellus Oils	2	2				
Tenol Oils	2					
Terpineol	2					
Tetrachloroethane	4	4	4	4		
Tetraethyl Lead	2	3		_		
Tetrahydrofuran	4	4 4	4	4		
Tetrahydroxydicyclopentadiene THF (Tetrahydrofuran)	4	4				
Thionyl Chloride	4	4			4	4
Titanium Tetrachloride	1	4			3	4
Toluol	4	4				
Tomatoes	1	1				
Tributyl Phsphate	4	4				
Trichloroethylene	4	4			3	4
Trichloroethane	4	4				
Tricesyl Phosphate	4	4			4	4
Triethanolamine Triethylamine	3	4 3				
Trihydroxybenzoic Acid	4	4				
Trimethylbenzene	4	4				
Trimethyl Propane	3	4				
Trinitrophenol	1					
Trisodium Phosphate	1	1			1	1
Tung Oil	2					
Turpentine	3	4			1	2
Ucon Hydrolube 150CP, 200CP	2					
Ucon Hydrolube 275CP, 300CP, 550CP	2					
Ucon M1	2					
Union Hydraulic Tractor Fluid	2	2				
Urea Urine	1	2			1	1
Varnish	4	4			1	2
Vegetable Oils	2	3	3	3		2
Versilube F-50, F-44	2	-	_	-		
Vinegar	1	2	2	2	2	3
Vinyl Acetate	4	4			4	4
Vinyl Chloride	4	4				
Vinyl Trichloride	4	4				
Vitrea Oils	2	_				
Vodka	1	2				
Water Acid - Mine Water Water in Oil Emulsions	1	1			2	4
Water (Distilled)	1	1			2	4
Water (Fresh)	1	1			2	4
Water (Salt)	1	1			2	4
Whiskey	1	2	2	2		
White Gasoline	1	1			1	2
White Liquor (Paper)	1	1				
Wines	1	2				
Wood Oil	1					
Xylene	4	4	3	3	2	3
Xylol	4	4			2	3
Yeast	1	2 2				
Yogurt Zeric	2	2				
Zinc (Chromate, Cyanide, Hydrate, Nitrate)	1	1			1	1
(, - , - ,						

TERMS, CONDITIONS AND LIMITED WARRANTY OF SALE

All prices, terms and conditions of sale are subject to MERCHANDISE SHIPPED IN ERROR change without prior notice. Buyer agrees to all terms and conditions of seller upon the placement of any and all purchase orders.

GENERAL

- All orders require a minimum charge of \$100.00.
- All claims must be made within seven (7) days of receipt of merchandise.
- The company reserves the right at all times to reject any and all orders for any reason.

PAYMENT TERMS

- Net 30 days (to approved and qualified accounts).
- We reserve the right to hold shipments against past due accounts.
- Seller may require full or partial payment in advance if, in its sole judgement, the financial condition of the buyer does not justify the terms specified.
- All past due accounts are subject to a late payment charge of 1.5% per month, or maximum allowed by law if different, along with the expenses incidental to collection including reasonable attorney's fees.
- Returned checks are subject to a minimum \$50.00 charge.

ACCEPTANCE, ALTERATION AND CANCELLATION OF ORDERS

Orders for other than standard items or standard lengths may not be cancelled after purchase has been committed, production scheduled or any costs incurred.

RETURN OF DEFECTIVE MERCHANDISE

Defective or failed material to be held at the buyer's premises until authorization has been granted by seller to return or dispose of merchandise. Merchandise to be returned for final inspection must be returned Freight Prepaid in the most economical way. Credit will be issued for material found to be defective upon our inspection based on prices at time of purchase.

Buyer must notify seller immediately on any merchandise shipped in error. Upon notification, merchandise is to be returned to seller either via truck on a Freight Collect basis, via carrier of our choice, or via UPS on a Freight Prepaid basis. Buyer will be reimbursed for cost of merchandise, plus any additional freight which may have been incurred due to shipping error.

MERCHANDISE ORDERED IN ERROR

Standard packaged merchandise only may be returned, provided that the merchandise is in the original buyer's possession not more than 30 days. If merchandise is accepted for return, merchandise must be returned Freight Prepaid, and buyer will be charged a minimum of 15% rehandling charge, plus a chargeback for outbound freight charges if the original order was shipped prepaid. Returns are not accepted for any merchandise that is specifically manufactured to meet the buyer's requirement of either specifications or large quantity.

DELIVERY. DAMAGES. SHORTAGES

Delivery to the initial common carrier shall constitute the delivery to the buyer. Our responsibility, insofar as transportation risks are concerned, ceases upon the delivery of the merchandise in good condition to such a carrier, and all the merchandise shall be shipped at the buyer's risk.

GOODS DAMAGED IN SHIPMENT

Upon receipt of shipment, any evidence of damage to original shipping package must be reported by the receiving party and a claim made with the delivering carrier upon receipt of shipment.

CONCEALED DAMAGE

Any evidence of damage to material shipped, upon the opening of the original shipping package, must be reported by the receiving party to and a claim made with the delivering carrier without delay.

LIMITED WARRANTY

The merchandise or products sold or distributed by Jason Industrial Inc. are warranted to our customers to be free from defects in material and workmanship at the time of shipment by us. All warranty claims shall be made within 90 days after we have shipped the merchandise. Our liability hereunder is limited to the purchase price of any merchandise proved defective, or, at our option, to the replacement of such merchandise upon its authorized return to us.

THIS WARRANTY IS IN LIEU OF AND EXCLUDES ALL OTHER WARRANTIES, EXPRESSED, IMPLIED, STATUTORY, OR OTHERWISE CREATED UNDER APPLICABLE LAW INCLUDING, BUT NOT LIMITED TO, THE WARRANTY OF MERCHANT ABILITY AND THE WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT SHALL WE BE LIABLE FOR SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES, INCLUDING LOSS OF PROFITS.





- Power Transmission Belting
- Sheaves, Pulleys & Accessories
 - Industrial Hose & Couplings
 - Skirtboard Rubber







Fairfield, NJ

Megadyne America

Charlotte, NC



Carol Stream, IL



Tampa, FL



Dallas, TX

Other Jason Industrial Locations:

- Sorocaba Sao Paulo Brazil
- Azcapotzalco, Mexico
- Mississauga, Ontario Canada
- Edmonton, Alberta Canada
- Dorval, Quebec Canada

Contact Jason Industrial for additional information. Visit us online at www.jasonindustrial.com

TBMC - Greenville, SC







MEGADYNE HEADQUARTERS

Via Trieste 16, 10075 Mathi (TO) - ITALY mail@megadyne.it www.megadyne.it

JASON HEADQUARTERS

340 Kaplan Drive Fairfield, NJ 07004 Ph: 973-227-4904 Fax: 973-227-1651 www.jasonindustrial.com



EUROPE MIDDLE EAST AFRICA

MATHI (Italy)*

VENICE (Italy) MILAN (Italy) MINSK (Belarus) PRAGUE (Czech Republic) PARIS (France) ST. JEANNE DE MAURIENNE (France)* LYON (France) BORCHEN (Germany) ULM (Germany) BUDAPEST (Hungary) BYDGOSZCZ (Poland) BARCELONA (Spain)* DUDLEY (U.K.) STOCKHOLM (Sweden)



AMERICAS

FAIRFIELD, NJ (U.S.A.) CAROL STREAM, IL (U.S.A.) BELL, CA (U.S.A.) TAMPA, FL (U.S.A.) DALLAS, TX (U.S.A.) PORTLAND, OR (U.S.A.) CHARLOTTE, NC (U.S.A.) GREENVILLE, SC (U.S.A.) DORVAL, Quebec (Canada) MISSISSAUGA, Ontario (Canada) EDMONTON, Alberta (Canada) AZCAPOTZALCO (Mexico) SAO PAULO (Brasil) SOROCABA (Brasil) CARTAGENA (Colombia) CORDOBA (Argentina) LIMA (Peru)

ASIA/PACIFIC

NINGBO (R.P.C.)* QINGDAO (R.P.C.)* SHANGHAI (R.P.C.) FOSHAN (R.P.C.)

*MANUFACTURING FACILITIES